

Bore No.	Depth Metres		INTERVAL METRES	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ % ²	Ag ppm	Au ppm	Remarks
	From	To													
SMD 6	21.35	22.75	1.4 metres	8	130	360	1600	-4	150	270	40	18.0			
6	22.75	23.50	0.75	14	580	640	1850	-4	170	310	30	19.0			
6	23.50	24.75	1.25	6	450	310	2000	-4	35	120	40	17.5			
6	24.75	26.15	1.4	12	640	400	1950	-4	95	100	40	19.4			
6	26.15	28.00	1.85	14	540	290	1050	-4	15	90	30	8.4			
6	28.00	29.15	1.15	10	720	440	2050	-4	28	130	30	16.0			
6	29.15	29.50	0.35	10	720	360	1250	6	38	130	20	28.5			
6	29.50	30.80	1.3	12	410	560	1950	-4	50	120	30	19.5			
6	30.80	32.15	1.35	14	230	290	760	6	12	50	50	8.6			
6	32.15	33.90	1.75	14	1050	880	1950	8	190	120	30	21.5			
6	33.90	34.50	0.6	16	380	390	1750	-4	10	42	30	9.2			
6	34.50	35.50	1.0	18	660	660	2100	-4	15	100	40	20.0			
6	35.50	36.40	0.9	12	700	880	3350	10	35	110	40	16.0			
6	36.40	38.00	1.6	12	480	640	2050	6	32	100	40	15.5			
6	38.00	39.00	1.0	20	640	210	2550	12	30	100	60	15.0			
6	39.00	40.00	1.0	12	860	900	1700	90	90	90	80	24.5			
6	40.00	41.00	1.0	12	1550	400	2700	80	35	60	40	21.5			
6	41.00	42.00	1.0	4	2650	680	1150	160	160	100	40	30.0			
6	42.00	43.00	1.0	6	4600	600	1300	110	50	120	40	30.0			
6	43.00	44.00	1.0	10	860	660	1200	75	48	140	30	24.5			
6	44.00	45.00	1.0	10	1100	470	1500	90	18	140	50	24.5			
6	45.00	46.00	1.0	12	600	700	1100	16	18	120	80	23.0			
6	46.00	47.00	1.0	6	980	700	1400	-4	15	150	30	20.5			
6	47.00	48.00	1.0	6	740	600	1100	16	18	160	30	20.5			
6	48.00	49.00	1.0	-4	940	600	1150	170	8	160	40	25.0			
6	49.00	50.00	1.0	8	1050	680	1050	14	18	160	40	24.5			
6	50.00	51.00	1.0	4	740	600	1050	24	32	220	30	15.5			
6	51.00	52.00	1.0	6	880	470	900	4	8	170	30	17.0			
6	52.00	53.00	1.0	-4	860	620	1000	-4	10	200	30	17.5			
6	53.00	54.00	1.0	12	840	440	1250	10	85	200	50	17.5			
6	54.00	55.00	1.0	-4	1000	390	1200	26	28	140	40	19.0			
6	55.00	56.00	1.0	10	1750	600	1650	34	85	110	30	20.5			
6	56.00	57.00	1.0	6	700	330	1700	42	28	110	30	16.0			

↑

S.M.D. 6

60 core samples
over 63.65 metres.

To be part of
50 Kg. composite
sample composed
of 308.7 gms
per metre of
core. length

↓

continued