

Core No.	Depth Metres		INTERVAL METRES	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ % ²	Ag ppm	Au ppm	Remarks
	From	To													
SMD 7	00.00	01.00	1.0 metres	16	880	680	2750	22	38	510	20	10.5			
7	01.00	08.00	7.0	14	800	420	2350	-4	12	280	20	25.5			
7	08.00	09.62	1.62	14	880	640	1400	-4	15	220	30	28.0			
7	09.62	11.00	1.38	4	1350	640	1350	16	28	250	30	28.0			
7	11.00	12.00	1.0	6	780	420	1650	-4	12	270	50	26.5			
7	12.00	13.00	1.0	6	330	390	1900	-4	10	360	50	21.5			
7	13.00	14.00	1.0	8	580	440	1550	4	12	370	50	21.5			
7	14.00	16.00	1.0	10	840	490	1300		20	370	50	23.5			
7	16.00	17.00	1.0	4	290	340	1300	16	10	320	80	17.7			
7	17.00	18.00	1.0	6	660	260	1400	6	2	270	50	19.5			
7	18.00	19.00	1.0	18	1100	320	1550	12	5	130	80	21.5			
7	19.00	20.00	1.0	14	840	540	1600	22	85	370	80	25.0			
7	20.00	21.00	1.0	8	800	640	1500	38	10	270	30	28.0			
7	21.00	21.75	0.75	6	920	470	2200	28	5	570	50	27.0			
7	21.75	22.65	0.9	16	390	130	2400	16	5	120	50	9.9			
7	22.65	24.00	1.35	12	1000	580	1800	20	5	170	80	22.5			
7	24.00	25.00	1.0	12	1550	420	1800	80	120	9800	30	24.5			
7	25.00	26.00	1.0	16	400	940	1300	30	230	740	30	20.5			
7	26.00	27.00	1.0	8	680	920	1500	26	440	450	30	21.5			
7	27.00	28.00	1.0	8	920	580	2500	60	220	410	40	22.5			
7	28.00	29.00	1.0	12	860	460	2250	95	85	310	40	22.0			
7	29.00	30.00	1.0	4	840	520	1700	46	110	1870	30	17.0			
7	30.00	31.00	1.0	8	1850	350	1400	46	38	180	40	23.0			
7	31.00	32.00	1.0	12	500	350	1050	50	110	160	40	23.0			
7	32.00	33.00	1.0	18	2150	390	2250	48	200	190	30	19.5			
7	33.00	34.00	1.0	-4	1300	240	2300	55	8	150	20	21.5			
7	34.00	35.00	1.0	12	720	680	1450	30	32	120	80	23.5			
7	35.00	36.00	1.0	14	940	230	2850	46	40	210	30	14.0			
7	36.00	37.00	1.0	12	1100	300	1800	70	60	110	30	20.5			
7	37.00	38.00	1.0	14	1950	470	880	70	130	110	50	22.0			
7	38.00	39.00	1.0	10	4500	500	1050	230	95	110	40	23.0			
7	39.00	40.00	1.0	4	3050	620	920	290	50	120	30	22.5			
7	40.00	41.00	1.0	8	1400	520	1000	80	55	170	80	21.0			

↑

Smd. 7.

40 core samples
over 48.56 metres

To be part of
50Kg. composite
sample composed
of 308.7 gms
per metre of
core length.

↓

continued