

437

221531

A-16

TABLE A-5: OVERALL TIN DISTRIBUTION BETWEEN GARNET AND CASSITERITE

	Distribution in Total Ore %	% in Garnet	% in Cassiterite
1. Tin in minus 9 $\mu$ m slimes	19	79	710
2. Tin in plus 9 $\mu$ m ferromagnetic products (i.e. locked with magnetite)	27	4	23
3. Tin in <3.3 sp.gr. products (i.e. locked with light gangue and fluorite)	19	3	16
4. Tin in plus 9 $\mu$ m >3.3 sp.gr. non-magnetic products (i.e. liberated cassiterite, cassiterite locked with dense gangue and liberated garnet)	35	26	9
Total	100	42	58