

PLATE A-1

a to d Photomicrographs of the non-magnetic 3.1 to 3.3 sp.gr. products (all 240×).

a. -75+33  $\mu\text{m}$

b. -75+33  $\mu\text{m}$

c. -33+17  $\mu\text{m}$

d. -17+9  $\mu\text{m}$

Fluorite in the material darker than the background; bright white material in lc is pyrite and light-grey material is garnet or amphibole. Much of the fluorite in the minus 33 plus 17- $\mu\text{m}$  fraction is liberated but in the minus 75 plus 33- $\mu\text{m}$  material a considerable amount of locked fluorite is present.