

(3)

Table II Heavy Liquid Separation of Size Fractions

Fraction	% Mass	Scheelite occurrence from (uv examination)
+2.36mm H/L F/T	0.2	nil
+2.36mm H/L S/K	trace	nil
+2.36mm	0.2	nil
+1.18mm H/L F/T	0.2	nil
+1.18mm H/L S/K	1.8	composite
+1.18mm	2.0	composite
+600µm H/L F/T	0.3	nil
+600µm H/L S/K	1.3	composite
+600µm	1.6	composite
+300µm H/L F/T	1.0	nil
+300µm H/L S/K	4.4	free
+300µm	5.4	-
+150µm H/L F/T	2.3	-
+150µm H/L S/K	13.4	free
+150µm	15.7	-
+75µm H/L F/T	3.9	-
+75µm H/L S/K	12.5	free
+75µm	16.4	-
+38µm	12.8	free
-38µm	45.9	-
HEAD	100	