

6 Flotation Concentrates

Chemical analysis of a sulphide composite made on a weighted basis from cleaner flotation concentrates from the four stages of concentration, was found to contain the followings:

<u>Element</u>	<u>Percent</u>
As	0.13
Sb	0.01
Bi	1.30
Pb	0.52
Cu	0.33
Zn	2.3
S	40.8
Mo	0.22
Fe	38.7