

112

SAMPLE NUMBER	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Mn ppm	Fe %
KD 3163	5	20	15	(2	190	0.20
4	(2	20	10	(2	5	0.02
5	5	20	15	(2	15	0.06
6	10	20	15	(2	35	0.18
7	2	20	20	(2	100	0.06
8	5	20	15	(2	80	0.04
9	2	(20	15	(2	5	0.02
70	2	(20	25	(2	110	0.05
1*	(2	(20	15	(2	85	0.04
2	2	20	20	(2	250	0.20
3	2	20	15	(2	10	0.02
4	(2	(20	10	(2	(5	0.01
5	(2	(20	10	(2	(5	0.01
6	(2	(20	15	(2	10	0.02
7	(2	(20	10	(2	85	0.16
8	2	20	30	(2	170	0.16
9	2	(20	10	(2	15	0.03
80	(2	(20	10	(2	40	0.04
1*	(2	(20	10	(2	25	0.03
2	(2	(20	10	(2	200	0.03
3	(2	(20	20	(2	840	0.11
4	(2	(20	5	(2	10	0.02
5	2	(20	10	(2	70	0.05
6	(2	(20	20	(2	60	0.05
7	(2	20	15	(2	80	0.04
8	(2	20	20	(2	230	0.05
9	(2	(20	10	(2	80	0.05
90	(2	20	10	(2	90	0.05
1*	(2	20	10	(2	75	0.05
2	(2	(20	10	(2	70	0.07
3	(2	20	5	(2	55	0.04
4	(2	(20	10	(2	100	0.08
5	(2	20	15	(2	200	0.11
6	(2	(20	10	(2	30	0.05
7	(2	(20	10	(2	90	0.06
8	(2	(20	10	(2	20	0.03
9	2	(20	10	(2	5	0.04
200	(2	(20	5	(2	15	0.04
1*	(2	(20	5	(2	10	0.05
2	(2	20	5	(2	25	0.06
3	(2	20	20	(2	100	0.58
4	(2	(20	25	(2	40	0.09
5	2	(20	10	(2	25	0.04
6	(2	(20	5	(2	35	0.04
7	(2	(20	5	(2	20	0.04
8	(2	(20	10	(2	30	0.05
9	(2	20	10	(2	25	0.06
10	2	(20	20	(2	20	0.07
1*	5	(20	15	(2	20	0.08
2	(2	(20	10	(2	5	0.02
3	5	30	110	(2	280	0.69
4	2	20	20	(2	420	0.14
5**	(2	(20	20	(2	490	0.13
5	(2	(20	20	(2	510	0.12
KD 3216	(2	20	20	(2	25	0.02

* Denotes duplicate of previous sample.

** Denotes repeat and check.

(Denotes less than.