

| SAMPLE NUMBER |        | Cu ppm | Pb ppm | Zn ppm | Ag ppm | Mn ppm | Fe % |
|---------------|--------|--------|--------|--------|--------|--------|------|
| KS            | 2408   | 2      | 20     | 15     | (2     | (5     | 0.12 |
|               | 9      | 10     | (20    | 10     | (2     | 5      | 0.12 |
|               | 10     | 5      | 20     | 15     | (2     | 10     | 0.44 |
| KS            | 2411 * | 5      | 20     | 10     | (2     | 10     | 0.44 |

PREPARATION: Dried and sieved to -80mesh.

ANALYTICAL METHODS: Cu, Pb, Zn, Ag, Mn and Fe by A.A.S. following hot conc. HCL . leach and HCL/HNO<sub>3</sub> leach in latter stages for 1 hour of 0.25 g sample.

\* Denotes duplicate of previous sample

•• Denotes repeat and check.

( Denotes less than.