

140

SAMPLE NUMBER		Cu ppm	Pb ppm	Zn ppm	Ag ppm	Mn ppm	Fe %
KS	3345	(2	(20	25	(2	20	0.08
	6	(2	(20	25	(2	20	0.19
	7	20	40	80	(2	340	0.89
	8	(20	(20	35	(2	310	0.72
	9	(20	(20	20	(2	110	2.10
	50	(20	(20	15	(2	5	0.08
	1	25	20	10	(2	55	0.32
	2	(2	(20	20	(2	370	0.27
	3	15	(20	15	(2	10	0.06
	4**	430	160	20	5	20	0.35
	4	450	140	30	5	20	0.32
	5	30	140	50	(2	10	0.13
	6	10	(20	5	(2	(5	0.18
	7	(2	40	10	(2	(5	0.09
	8	40	(20	5	(2	(5	0.10
	9	10	120	10	(2	(5	0.09
	60	5	40	5	(2	5	0.06
	1*	5	20	10	(2	(5	0.06
	2	(2	40	5	(2	5	0.05
	3	10	20	10	(2	10	0.44
	4	100	260	25	(2	75	0.86
	5	15	20	30	5	45	1.52
	6	20	50	80	(2	35	0.68
	7	55	120	10	(2	120	1.39
	8	20	60	100	(2	55	0.97
	9	10	40	10	(2	50	0.57
	70	20	40	65	(2	150	1.04
	1** *	20	40	55	(2	160	1.06
	1	20	60	60	(2	160	1.03
	2	35	180	350	(2	1350	0.86
	3	5	80	10	(2	35	0.26
	4	(2	(20	180	(2	35	0.19
	5	(2	(20	30	(2	20	0.37
	6	(2	(20	10	(2	15	0.14
	7	5	20	5	(2	20	0.15
	8	(2	30	20	(2	(5	0.05
	9	10	(20	55	(2	25	0.51
	80	5	(20	20	(2	40	0.24
	1	5	(20	15	(2	70	0.23
	2*	2	(20	10	(2	70	0.22
	3	20	(20	10	(2	95	0.71
	4	5	(20	20	(2	30	0.11
	5	20	60	15	(2	45	0.29
	6	10	20	30	(2	55	0.19
	7	130	72	80	(2	120	1.40
	8	(2	40	10	(2	25	0.48
	9	5	(20	15	(2	170	0.44
	90	60	(20	80	(2	75	1.04
	1*	40	40	95	(2	70	0.89
	2	5	(20	10	(2	10	0.15
	3	85	60	40	(2	2000	3.12
	4	5	(20	(2	(2	(5	0.07
	5	10	(20	55	(2	10	0.14
	6	5	20	10	(2	10	0.30
KS	3397	40	(20	190	(2	(5	0.20

● Denotes duplicate of previous sample.

● ● Denotes repeat and check.

( Denotes less than.