

SAMPLE NUMBER		Cu ppm	Pb ppm	Zn ppm	Ag ppm	Mn ppm	Fe %
KS	3874	10	60	15	(2	5	0.07
	5	10	20	30	(2	110	1.15
	6	(2	20	40	(2	290	2.00
	7	10	40	180	(2	600	3.25
	8	140	20	85	(2	800	5.00
	9	20	50	50	(2	550	2.15
	80	10	20	35	(2	350	1.00
	1**	5	(20	30	(2	340	0.98
	1	(2	(20	15	(2	45	0.25
	2	30	(20	90	(2	450	2.50
	3	30	60	130	(2	550	1.80
	4	25	40	60	(2	500	2.15
	5	30	30	85	(2	630	2.00
	6	5	50	95	(2	710	1.95
	7	20	40	70	(2	590	1.88
	8	(2	20	20	(2	15	0.12
	9	5	20	190	(2	10	0.14
	90	(2	180	400	(2	70	0.68
	1	10	160	400	(2	65	0.66
	2	(2	90	80	(2	130	1.13
	3	10	20	280	(2	340	2.40
	4	10	20	95	(2	270	1.95
	5	5	120	75	(2	580	1.45
	6	10	20	10	(2	20	1.13
	7	(2	20	40	(2	50	0.64
	8	(20	(20	10	(2	(5	0.07
	9	(20	(20	15	(2	20	0.09
	900	20	(20	15	(2	60	0.07
	1	20	40	10	2	10	0.18
	2	20	(20	10	5	25	0.59
	3**	(20	120	90	(2	20	0.56
	3	20	140	100	(2	20	0.52
	4	(20	50	100	(2	290	3.10
	5	20	240	120	(2	130	1.84
	6	60	30	70	(2	320	1.76
7	20	60	10	5	(5	0.10	
8	20	180	370	(2	25	0.20	
9	20	40	100	(2	35	0.35	
10	20	20	180	2	220	1.27	
KS	3911*	20	50	130	(2	230	1.36

PREPARATION:

Dried and sieved to -80 mesh.

ANALYTICAL METHODS:

Cu, Pb, Zn, Ag, Mn and Fe by A.A.S. following hot conc. H.C.L. leach and H.C.L/H.N.O<sub>3</sub> leach in latter stages for 1 hour of 0.25g sample.

● Denotes duplicate of previous sample.

●● Denotes repeat and check.

( Denotes less than.