



LEGEND

Pb, Zn
Cu, Co
Mn, Fe
Sn

Samples were dried and sieved to -80 mesh. Base metals were analysed by A.A.S. after digestion in nitric/perchloric acid. Sn was analysed by A.A.S. after fusion with ammonium iodide.

>300ppm Pb is highly anomalous
200-300 ppm Pb is weakly anomalous

>300ppm Zn is highly anomalous
200-300 ppm Zn is weakly anomalous

1	2
3	4
5	6
28	7
30	9
32	11

5 cm

ELECTROLYTIC ZINC CO. OF ASIA, LTD.
PROJECT: MT. BLACK TAS

055555
GEOCHEMISTRY
Stream Sediment Samples -80#
Zn

SCALE: 1:10 000	Survey: J. McD.	Revised: 1. 9. 80
Reference:	Date: 18. 3. 80	REF NO.
Drawn: R.P.T.	Checked:	AO-525-0091