

Four sets of reserves have been calculated on a section by section basis. A 0.3% Sn cut-off was used for the dolomite sulphide lode, and 0.2% Sn, 0.3% Sn and 0.4% Sn cut-off for the porphyry. The following summary includes indicated and inferred ore:

Rock Type	Cut-off Grade % Sn	Tonnes	Grade % Sn	Contained Tin (tonnes)
Dolomite Sulphide Lode	0.3	1,299,000	1.06	13,770
Porphyry	0.2	3,259,000	0.47	15,320
Porphyry	0.3	2,433,000	0.54	13,140
Porphyry	0.4	1,490,000	0.67	9,980

The dolomite sulphide lode would be amenable to open pit mining at an overburden ratio of about 4 or 5:1. About 250,000 tonnes of porphyry ore would lie within the pit, and the rest would be mined by underground methods. An annual mining rate of 300,000 tonnes could be expected.

Approximate figures for ore mined, dilution, waste and ore left in pillars have been calculated for the 0.3% Sn cut-off grade for the dolomite sulphide lode and the porphyry: