

4. SURFACE SAMPLINGSlaughteryard Face

The Dolomite Sulphide Lode was chip sampled on two lines, 20 metres apart. Each sample weighed about 4kg and covered 10 metres on each line. The chips were taken laterally within 1 metre of the line. The following results were obtained:

LINE NUMBER	FROM	TO	WIDTH (m)	%Sn
1040E	2110N	2180N	70	0.84
1060E	2110N	2180N	70	1.23

One sample was of low grade, 900 ppm Sn, but the other samples assayed between 0.33% Sn and 3.26% Sn.