

Dolomite Sulphide Lode Metal Grades

(in ppm)

HOLE NUMBER	Cu	Pb	Zn	Ag	W	As	NO. OF SAMPLES
MBD 15	130	70	950	1.3	20	160	4
MBD 16	490	180	2760	2.3	70	1170	9
MBD 17	380	170	6420	1.7	30	1340	11
MBD 18	1070	120	290	0.4	200	6020	13
MBD 19	550	40	1500	2.0	35	2000	1
MBD 20	440	130	670	4.3	50	4660	8
MBD 21	110	10	2600	0.3	30	860	3
MBD 22	660	20	150	-	80	280	10
MBD 23	420	80	390	0.4	40	90	11
MBD 27	250	30	100	-	20	270	9
MBD 29	510	30	720	0.5	50	310	2
MBD 29A	1080	1330	2900	8.5	210	16730	4
MBD 31	680	190	6430	1.3	50	1630	10
AVERAGE	520	180	1990	1.8	70	2730	95
WEIGHTED AVERAGE	560	160	2120	1.5	70	2490	95