

The assay results for the metallurgical samples are summarized in the accompanying tables (pages D1 and D2 taken from AMDEL's metallurgical reports). A comparison of the head assays of each sample with the calculated head assays from the individual 2 metre core samples is as follows:

SAMPLE NUMBER	ROCK TYPE	DRILL HOLE	INTERVAL (m)	HEAD ASSAY % Sn	CALCULATED HEAD ASSAY % Sn
97528	Porphyry	MBD 14	9.2-24.8	0.23	0.23
97529	Porphyry	MBD 15	43.3-55.8	0.26	0.23
97530	Porphyry	MBD 16	23.0-55.9	0.26	0.29
97531	Porphyry	MBD 17	15.9-31.9	0.33	0.36
97532	Dolomite	MBD 17	59.6-70.6	0.34	0.37
97533	Dolomite	MBD 18	5.7- 6.9 and 8.8-29.3	2.38	1.88
97534	Dolomite	MBD 20	18.7-32.3	0.61	0.53
97535	Dolomite	MBD 23	7.3-25.1 and 35.7-40.6	1.72	1.36

The specific gravity measurements were obtained using an Air Comparison Pycnometre on minus 1.7mm (minus 10 mesh) crushed material.