

## APPENDIX D

## HEAD ASSAYS AND SPECIFIC GRAVITY MEASUREMENTS

Sample	Assay								Specific Gravity
	Sn %	Acid Soluble Sn %	S %	Fe %	F %	CO <sub>2</sub> %	U g/t	Hg g/t	
97528	0.23	0.02	9.70	3.65	6.00	<0.05	14	-	2.96
97529	0.26	0.02	11.6	6.50	7.30	1.55	15	-	3.01
97530	0.26	0.02	15.1	4.70	5.50	0.15	15	-	2.98
97531	0.33	0.02	15.1	4.85	5.70	0.10	14	-	3.00
97532	0.34	0.02	44.1	23.6	13.8	3.25	4	-	3.43
97533	2.38	0.09	72.3	31.9	11.1	1.75	4	-	3.78
97534	0.61	0.10	37.7	21.5	0.86	16.6	4	-	3.33
97535	1.72	0.02	37.7	21.0	8.25	4.05	4	-	3.38
PC1	0.24	0.02	10.5	5.00	6.20	1.25	14	0.14	3.03
PC2	0.29	0.02	14.9	4.65	5.90	0.10	16	0.05	3.04
SC1	1.40	0.05	53.0	27.4	12.8	3.10	<4	0.09	3.61
SC2	1.20	0.01	38.1	21.5	4.70	10.7	<4	0.07	3.40

Element	Semi-quantitative Spectrographic Analysis, g/t			
	PC1	PC2	SC1	SC2
Ba(200)	X	X	X	X
Be(1)	3	20	150	100
Ce(300)	X	X	X	X
Co(5)	X	X	X	15
Cr(20)	150	150	40	30
La(50)	X	X	X	X
Mn(10)	1,000	80	800	4,000
Mo(3)	6	3	X	X
Nb(20)	40	20	X	X
Ni(5)	30	30	X	5
Sc(3)	3	3	3	X
Sr(50)	X	X	X	X
Ta(100)	X	X	X	X
Th(100)	X	X	X	X
Ti(100)	200	200	100	100
V(10)	15	15	25	15