

TABLE B7: (Continued)

Sample	Size Fraction (μm)	% Lib. Cassit.	% Locked in Binary Grains With				% Locked in Ternary ⁽⁺⁾ Grains
			Non-op. Gangue	Fe-Ti Oxides	Pyrite	Pyrrhotite	
Sulphide Comp. 2 (SC2)	+500	22	60	-	-	-	18
	-500 +300	53	35	2	-	4	6
	-300 +210	57	35	1	-	3	4
	-210 +105	76	19	1	-	1	3
	-105 + 53	79	19	-	-	1	1
Total Heavy Pr.		(51)	(39)	(1)	(-)	(1)	(8)