

(c) Comments

- (i) Coarse grind of 100% -150 μm gave a tin extraction of 5% lower than that of the finer grind of 100% -75 μm .
- (ii) It appeared liberation of tin mineral at a grind size of 150 μm was only slightly poorer than that of 75 μm .
- (iii) Extra tin losses in tailing could be due to either coarse free or composite grains tin mineral.