

(c) Comments

- (i) Tin losses in sulphide concentrate product improved with flotation cleaning in which an additional close to 6% (assayed 2.44% Sn) of the total tin was recovered.
- (ii) Tin recovery in tin rougher concentrate (73.33%) was satisfactory with 30 min. flotation time and 1.6 kg/t of collector PTAA as compared to Test SC1/F1 of 60 min. and 2.6 kg/t at 74.72% recovery.