

- (ii) The overall tin recovery of the rougher concentrate in this test was as high as that using collectors PTAA and SPA in Tests SC1/F3 and F4. However, the rougher concentrate grade was about half of that obtained in the previous tests.
- (iii) This test revealed that collector S-3903 was applicable to tin flotation treatment of Composite SC1 but not for the other three composite ore samples using similar flotation conditions.