

TABLE J3: TIN DISTRIBUTION IN THE LEACH RESIDUES OF THE TABLE/SUPERPANNER SIZE FRACTIONS

Sample	Original Size USS Mesh	Fractions μm	Size Fractions After Leaching μm		Wt. %	Sn	
						Assay, %	Distn. %
PC1/BF	-60+100	-250+150	+100	+150	60.7	48.7	86.3
			-100+200	-150+75	20.4	17.4	10.3
			-200+300	-75+53	5.0	9.50	1.4
			-300	-53	13.9	4.82	2.0
			Total		100.0	(34.3)	100.0
PC1/BF	-200+300	-75+53	+300	+53	91.6	49.2	97.4
			-300	-53	8.4	14.2	2.6
			Total		100.0	(46.3)	100.0
PC2/BF	-60+100	-250+150	+100	+150	64.2	24.3	87.8
			-100+200	-150+75	21.3	6.1	7.7
			-200+300	-75+53	4.3	6.96	1.7
			-300	-53	10.2	4.88	2.8
			Total		100.0	(17.8)	100.0
PC2/BF	-200+300	-75+53	+300	+53	86.9	16.17	94.4
			-300	-53	13.1	6.40	5.6
			Total		100.0	(14.9)	100.0
SC1/BF	-60+100	-250+150	+100	+150	40.9	47.0	56.4
			-100+200	-150+75	40.9	24.1	28.9
			-200+300	-75+53	9.1	23.1	6.2
			-300	-53	9.1	31.9	8.5
			Total		100.0	(34.1)	100.0
SC1/BF	-200+300	-75+53	+300	+53	90.7	21.7	89.9
			-300	-53	9.3	23.7	10.1
			Total		100.0	(21.9)	100.0
SC2/BF	-60+100	-250+150	+100	+150	89.9	72.1	92.1
			-100+200	-150+75	8.0	60.3	6.8
			-200+300	-75+53	1.4	32.8	0.7
			-300	-53	0.7	35.3	0.4
			Total		100.0	(70.3)	100.0
SC2/BF	-200+300	-75+53	+300	+53	94.8	68.6	94.8
			-300	-53	5.2	68.8	5.2
			Total		100.0	(68.6)	100.0