

Element	Semi-quantitative Spectrographic Analysis g/t	
	PC1/HG Superpanner Tin Conc	PC2/HG Superpanner Tin Conc
Ba(200)	X	X
Be(1)	1	2
Ce(300)	500	800
Co(5)	10	X
Cr(20)	80	80
La(50)	250	400
Mn(10)	3,000	600
Mo(3)	10	6
Nb(20)	X	X
Ni(5)	200	50
Sc(3)	X	X
Sr(50)	X	X
Ta(100)	X	X
Th(100)	X	X
Ti(100)	6,000	10,000
V(10)	50	80
W(50)	10,000	>10,000
Y(10)	250	1,500
Yb(1)	60	100
Zr(10)	250	400
Ag(0.1)	5	20
As(50)	4,000	4,000
Bi(1)	25	25
Cd(3)	X	X
Cu(1)	100	1,000
Ga(1)	60	60
Ge(1)	2	3
In(10)	60	30
Pb(1)	400	800
Sb(30)	30	30
Sn(1)	>>10,000	>>10,000
Zn(20)	250	60
Au(3)	30	5
P(100)	X	X
Te(20)	X	X
Tl(1)	X	X
Al(100)	>10,000	>10,000
Ca(100)	1,000	200