

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
96428		19.8	21.8	2.0	3300									
29		21.8	23.8	"	310									
30		23.8	25.8	"	2200									
31		25.8	27.8	"	1.86%									
32		27.8	29.0	1.2	1.32%									
33		31.7	33.7	2.0	1.63%									
34		33.7	35.7	"	2.12%									
35		35.7	37.7	"	3700									
36		37.7	39.7	"	680									
37		39.7	41.7	"	100									
38		41.7	43.7	"	75									
39		43.7	45.7	"	16									
96440		45.7	48.2	2.5	12									

Notes — XRF Bi Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. B1
 SAMPLE TYPE : DRILL CORE FROM 19.8 TO 48.2

028277