

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn ppm	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
95500		352.9	355.0	2.1	46		75	12	22	<1	10			
1		355.0	357.5	2.5	85		40	5	15	<1				
2		357.5	360.0	2.5	150		270	8	22	<1				
3		360.0	361.5	1.5	46		120	8	15	<1				
4		361.5	362.5	1.0	46		65	5	12	<1				
5		362.5	365.0	2.5	48		55	5	12	<1	<10			
6		365.0	367.5	2.5	38		55	8	15	<1				
7		367.5	370.0	"	250		140	8	15	<1				
8		370.0	372.5	"	46		200	10	15	<1				
9		372.5	375.0	"	46		230	5	10	<1				
10		375.0	377.5	"	30		240	5	8	<1	15			
11		377.5	380.0	"	34		280	12	8	<1				
12		380.0	382.5	"	580		370	50	80	1				
13		382.5	385.0	"	2050		270	8600	3.8%	15				
14		385.0	387.5	"	210		160	460	1250	2				
15		387.5	389.0	"	85		65	55	55	<1	25			
16		389.0	390.3	1.3	50		60	38	48	<1				
17		390.3	392.5	2.2	75		48	75	80	<1				
18		392.5	395.0	2.5	85		140	80	50	<1				
19		395.0	397.5	"	30		70	40	55	<1				
20		397.5	400.0	"	230		500	70	150	1	30			
21		400.0	402.5	"	150		45	35	20	<1				
22		402.5	405.0	"	50		50	30	20	<1				
23		405.0	407.5	"	110		65	18	35	<1				
24		407.5	410.0	"	34		32	8	22	<1				
25		410.0	412.5	"	55		80	10	18	<1	10			
26		412.5	415.0	"	38		70	18	15	<1				
27		415.0	417.5	"	150		210	90	170	1				
28		417.5	420.0	"	80		48	28	18	<1				
95529		420.0	422.5	"	42		38	15	35	<1				

Notes:- W & Sn by XRF B1 METHOD.
Cu, Pb, Zn, Ag by AAS.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
ASSAY SUMMARY SHEET HOLE NO. B9A

SAMPLE TYPE : DRILL CORE FROM 352.9 TO 422.5

028298