

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn ppm	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
95530		~422.5	~425.0	2.5	28		28	5	20	<1	<10			
31		~425.0	~427.5	"	36		28	8	20	<1				
32		~427.5	~430.0	"	110		48	5	15	<1				
33		~430.0	432.5	"	760		95	30	25	<1				
34		432.5	435.0	"	500		180	20	12	<1				
35		435.0	437.5	"	85		75	18	22	1	<10			
36		437.5	440.0	"	60		48	15	35	1				
37		440.0	442.5	"	70		80	10	18	1				
38		442.5	445.0	"	50		100	18	20	1				
39		445.0	447.5	"	38		55	25	12	1				
40		447.5	450.0	"	1050		110	160	1300	2	20			
41		450.0	452.5	"	65		45	25	48	1				
42		452.5	455.0	"	40		40	22	15	1				
43		455.0	457.5	"	34		25	25	20	1				
44		457.5	460.0	"	26		30	20	25	1				
45		460.0	462.5	"	160		50	35	65	1	<10			
46		462.5	464.8	2.3	42		70	45	110	1				
47		464.8	465.7	.9	170		200	80	520	1				
48		465.7	467.6	1.9	60		100	50	65	1				
49		467.6	~469.3	1.7	60		45	32	40	1				
50		~469.3	~471.3	2.0	32		20	40	60	1	<10			
51		~471.3	473.4	2.1	38		25	45	25	1				
52		473.4	475.0	1.6	55		35	140	35	1				
53		475.0	477.5	2.5	40		30	45	240	1				
54		477.5	480.0	"	34		48	22	10	1				
55		480.0	482.5	"	34		50	35	100	1	<10			
56		482.5	485.0	"	42		65	32	25	1				
57		485.0	487.5	"	70		80	25	12	1				
58		487.5	490.0	"	75		50	12	12	1				
95559		490.0	492.5	"	50		38	8	22	1				

Notes:— W, Sn, by XRF BI METHOD.
Cu, Pb, Zn, Ag A.A.S.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
ASSAY SUMMARY SHEET HOLE NO. 89B

SAMPLE TYPE : DRILL CORE FROM ~422.5 TO 492.5.

028299