

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
98122		31.4	33.4	2.0	1050									
23		33.4	35.4	"	70									
24		35.4	37.4	"	14									
25		37.4	39.4	"	14									
26		39.4	41.4	"	440									
27		41.4	43.7	2.3	75									
28		43.7	45.6	1.9	640									
95186		~ 66.1	~ 70.0	3.9	210		40	20	430	1				
87		70.0	72.5	2.5	200		20	300		2				
88		72.5	75.0	"	36		25	15	45	1				
89		75.0	77.5	"	12		12	5	50	1				
90		77.5	80.0	"	12		70	12	48	2				
91		80.0	82.5	"	38		38	12	45	2				
92		82.5	85.0	"	1350		980	950	1.0%	14				
93		85.0	87.5	"	100		50	45	230	1				
94		87.5	90.0	"	40		38	42	1350	1				
95		90.0	92.5	"	28		22	18	260	1	210			
96		92.5	95.0	"	65		22	12	190	1				
97		95.0	97.5	"	44		25	22	190	1				
98		97.5	100.0	"	100		130	2300	1850	3				
99		100.0	102.5	"	480		90	210	160	2				
95400		102.5	105.0	"	100		25	25	140	21	210			
1		105.0	107.5	"	55		18	12	100	21				
2		107.5	110.0 <sup>HP</sup>	"	300		45	22	200	21				
3		110.0 <sup>HP</sup>	112.5 <sup>HP</sup>	"	190		160	80	630	2				
4		112.5 <sup>HP</sup>	115.0 <sup>HP</sup>	"	660		95	1900	4000	2				
5		115.0 <sup>HP</sup>	117.5 <sup>HP</sup>	"	760		140	2400	3.6%	32	210			
6		117.5 <sup>HP</sup>	120.0	"	1850		140	170	1350	1				
7		120.0	122.83	2.83	240		350	48	110	21				

Notes:— Sn by XRF Bi Method.  
Cu, Pb, Zn, Ag by AAS.

METALS EXPLORATION LTD - MT. BISCHOFF TIN PROSPECT

ASSAY SUMMARY SHEET HOLE NO. B22 A

SAMPLE TYPE: DRILL CORE

FROM 31.4 TO 45.6

02832