

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
95408		122.83	125.0	2.17	470		90	15	520	<1				
95409		125.0	126.5	1.5	200		55	22	140	<1				
95409		126.5	130.0	3.5	46		42	40	410	<1				
10		130.0	133.5	"	2950		490	60	170	2	10			
11		133.5	135.0	1.5	1600		170	45	620	<1				
12		135.0	137.5	2.5	310		80	25	210	<1				
13		137.5	140.0	"	16		30	12	35	<1				
		140.0	142.5	"	8		28	10	35	<1				
15		142.5	145.0	2.5	18		28	5	35	<1	210			
16		145.0	147.22	2.22	26		22	5	22	<1				

Notes:— W and Sn by XRF B. Method.
 Cu, Pb, Zn, Ag by HAS

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. B22 B.
 SAMPLE TYPE : DRILL CORE FROM 122.83 TO 147.22

028325