

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
98129		12.8	14.8	2.0	310									
30		14.8	16.8	"	130									
31		16.8	18.8	"	480									
32		18.8	20.8	"	220									
33		20.8	22.8	"	180									
34		22.8	24.8	"	190									
35		24.8	26.8	"	560									
36		26.8	28.8	"	800									
37		28.8	30.8	"	140									
38		30.8	32.8	"	280									
39		32.8	34.8	"	210									
140		34.8	36.8	"	160									
41		36.8	38.8	"	370									
42		38.8	40.8	"	130									
43		40.8	42.8	"	18									
44		42.8	44.8	"	42									
45		44.8	46.8	"	120									
46		46.8	48.8	"	110									
47		48.8	51.2	2.4	160									
95828		75.9	77.5	2.6	95		28	12	60	2				
29		77.5	80.0	2.5	70		35	60	1.1%	6				
30		80.0	82.5	"	60		30	100	530	2	10			
31		82.5	85.0	"	160		60	15	180	2				
32		85.0	87.5	"	14		15	45	35	2				
33		87.5	90.0	"	540		48	130	40	6				
34		90.0	92.5	"	22		18	45	30	1				
35		92.5	95.0	"	44		20	5	50	1	10			
36		95.0	97.5	"	20		60	5	25	2				
37		97.5	100.0	"	370		70	28	200	2				

Notes: — Sn by XRF Bi Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. B23 A
 SAMPLE TYPE: DRILL CORE FROM 12.8 TO 100.00

028331