

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
95840		0.0	0.7	.7	80		10	20	90	<1				
41		0.7	2.5	1.8	14		75	30	220	<1				
42		2.5	5.0	2.5	160		8	12	660	<1				
43		5.0	6.3	1.3	130		2	10	590	<1				
44		8.1	9.1	1.0	560		15	80	890	<1				
45		9.5	12.3	2.8	720		45	60	610	<1				
46		13.0	13.8	.8	1750		70	32	1800	<1				
95897		14.1	14.7	.6	1350		22	12	370	<1				
95847		15.3	15.5	} 1.9	100		20	12	480	<1				
		15.8	17.5											
48		17.5	20.0	2.5	12		2	10	120	<1				
49		20.0	21.5	} 2.2	4		2	12	370	<1				
		21.8	22.5											
50		22.5	25.00	2.5	210		48	110	2800	3				
51		25.0	27.50	"	28		5	280	600	3				
52		27.5	30.0	"	55		2	65	220	2				
53		30.0	31.85	1.85	18		2	22	180	2				
54		32.23	33.20	.97	48		2	100	780	2				
55		33.50	34.60	1.1	110		18	45	560	2				
95898		35.20	36.00	0.80	30		10	38	1600	2				

028369

Notes:— W & Sn by XRF B. Method

Cu, Pb, Zn, Ag by AAS.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT

ASSAY SUMMARY SHEET HOLE NO. AAB 5

SAMPLE TYPE : DRILL CORE FROM 0.0 TO 36.00

A