

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
95856		36.50	39.50	3.0	6		20	25	1800	2				
57		39.50	42.50	"	16		28	18	1750	2				
58		42.50	44.50	2.0	360		65	60	920	3				
59		47.20	47.50	0.30	980		120	70	1200	<1				
60		54.90	56.30	1.4	55		12	18	160	<1	120			
61		56.80	57.80	1.0	80		12	48	1700	<1				
62		58.00	58.10	0.50	110		15	220	2100	21				
		58.20	58.60											
95899		59.10	60.00	0.40	<4		2	28	35	<1				
63		60.00	62.50	2.5	20		5	60	250	<1				
64		62.50	64.20	2.3	12		8	32	700	<1				
		64.40	66.00											
65		65.00	66.30	2.1	38		10	25	1300	<1	<10			
		66.70	67.50											
66		68.40	70.10	1.70	30		10	38	770	<1				
67		70.30	72.50	2.2	4		8	22	230	<1				
68		72.50	75.00	2.5	<4		5	20	48	<1				
69		75.00	76.10	2.30	4		10	120	1700	<1				
		76.20	76.40											
		76.50	77.50											

028370

Notes:— Sn by XRF B. Method
Cu, Pb, Zn, Ag by AAS.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT **B**
ASSAY SUMMARY SHEET HOLE NO. AAB5
SAMPLE TYPE : DRILL CORE FROM 36.50 TO 77.50