

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97700		3.0	5.0	2.0	1.46%		250	95	1000	2	35	85	1.04%	Re check of check Assay
1		5.0	7.0	"	3000		130	120	2100	1	30	150		
2		7.0	9.0	"	800									
3		9.0	11.0	"	740									
4		11.0	12.8	1.8	340									
5		14.6	16.6	2.0	65									
6		16.6	18.6	"	140									
7		18.6	20.6	"	4									
97708		20.6	22.6	2.0	65									
09		22.6	23.9	1.3	10									
96441		24.0	26.0	2.0	150									
42		26.0	28.0	"	240									
43		28.0	30.0	"	42									
44		30.0	32.0	"	22									
45		32.0	34.0	"	230									
46		34.0	35.28	1.28	400									
47		35.28	37.28	2.0	840		140	28	810	1	15	25		
48		37.28	39.28	"	520		110	10	1300	1	15	10		
49		39.28	41.28	"	640		150	22	2800	1	30	55		
450		41.28	43.28	"	920		200	20	720	1	45	300		
51		43.28	45.28	"	5100		280	70	190	2	70	800		
52		45.28	47.28	"	1000		190	20	1000	2	25	620		
53		47.28	49.28	"	1750		240	46	100	2	30	230		
54		49.28	51.28	"	1950		200	10	110	2	40	580		
55		51.28	53.28	"	2550		130	45	120	3	35	460		
56		53.28	55.82	2.54	1700		140	75	180	1	15	95		
57		55.82	57.82	2.0	2750		16	X	240	1	25	170		

Notes:— Sn by XRF B1 Method
 X means less than detection limit
 Results above 1.00% B2 Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT

ASSAY SUMMARY SHEET HOLE NO. MBD 15

SAMPLE TYPE: DRILL CORE FROM 3.0 TO 57.82

028379