

| SAMPLE NO. | SAMPLE NO | FROM | TO | INTER-VAL | Sn | Sn | Cu | Pb | Zn | Ag | W | As | Check Sn | Bulked Assays |
|------------|-------------|------|------|-----------|-------|--------|-----|-----|-------|----|-----|------|----------|---------------|
| SPLIT CORE | GROUND CORE | m | m | m | SPLIT | GROUND | | | | | | | | |
| 46469 | | 3.0 | 5.0 | 2.0 | 580 | | | | | | | | | |
| 70 | | 5.0 | 7.0 | " | 4000 | | | | | | | | | |
| 71 | | 7.0 | 9.0 | " | 720 | | | | | | | | | |
| 72 | | 9.0 | 11.0 | " | 640 | | | | | | | | | |
| 73 | | 11.0 | 13.0 | " | 620 | | | | | | | | | |
| 74 | | 13.0 | 15.0 | " | 4550 | | 85 | 85 | 4200 | 1 | 45 | 65 | | |
| 75 | | 15.0 | 17.0 | " | 560 | | 85 | 330 | 4400 | 1 | 55 | 180 | | |
| 76 | | 17.0 | 19.0 | " | 5900 | | 460 | 160 | 5400 | 2 | 65 | 1250 | | |
| 77 | | 19.0 | 21.0 | " | 2.14% | | 640 | 160 | 3500 | 2 | 95 | 620 | | |
| 78 | | 21.0 | 23.0 | " | 2.14% | | 660 | 360 | 5100 | 3 | 80 | 230 | | |
| 79 | | 23.0 | 25.0 | " | 740 | | 300 | 140 | 290 | 1 | 75 | 1200 | | |
| 480 | | 25.0 | 25.6 | 0.6 | 680 | | 300 | 33 | 110 | 1 | 40 | 560 | | |
| 81 | | 25.6 | 28.1 | 2.5 | 1.52% | | 410 | 255 | 5800 | 2 | 60 | 860 | | |
| 82 | | 28.1 | 30.1 | 2.0 | 760 | | 120 | 320 | 2500 | 2 | 20 | 140 | | |
| 83 | | 30.1 | 32.1 | " | 210 | | 48 | 290 | 320 | 1 | 15 | 25 | | |
| 84 | | 32.1 | 34.1 | " | 1150 | | 170 | 840 | 1.30% | 8 | 30 | 180 | | |
| 85 | | 34.1 | 36.1 | " | 520 | | 270 | 220 | 290 | 10 | 10 | 320 | | |
| 86 | | 36.1 | 38.1 | " | 6700 | | 430 | 760 | 2200 | 21 | 60 | 580 | | |
| 87 | | 38.1 | 40.1 | " | 5600 | | 560 | 350 | 1700 | 21 | 30 | 960 | | |
| 88 | | 40.1 | 42.1 | " | 2450 | | 530 | 180 | 1000 | 12 | 30 | 1750 | | |
| 89 | | 42.1 | 44.1 | " | 3400 | | 390 | 190 | 330 | 8 | 30 | 1350 | | |
| 490 | | 44.1 | 46.1 | " | 2350 | | 320 | 150 | 490 | 7 | 35 | 370 | | |
| 91 | | 46.1 | 48.1 | " | 430 | | 230 | 300 | 3100 | 7 | 15 | 40 | | |
| 92 | | 48.1 | 50.1 | " | 500 | | 260 | 660 | 1500 | 7 | 25 | 110 | | |
| 93 | | 50.1 | 52.1 | " | 660 | | 200 | 640 | 450 | 9 | 15 | 45 | | |
| 94 | | 52.1 | 54.1 | " | 2000 | | 210 | 140 | 360 | 9 | 10 | 35 | | |
| 95 | | 54.1 | 55.9 | 1.8 | 2000 | | 240 | 70 | 200 | 2 | 25 | 490 | | |
| 96 | | 55.9 | 57.9 | 2.0 | 1.26% | | 640 | 100 | 330 | 1 | 110 | 3050 | | |
| 97 | | 57.9 | 58.2 | 0.3 | 1.25% | | 670 | 100 | 630 | 1 | 65 | 2500 | | |
| 46498 | | 58.2 | 59.5 | 1.3 | 7500 | | 560 | 180 | 860 | 8 | 50 | 1460 | | |

028384

Notes: — Sn by XRF BI Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT A
ASSAY SUMMARY SHEET HOLE NO. MBD 16

SAMPLE TYPE : DRILL CORE FROM 3.0 TO 59.5