

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97142		0.0	2.0	2.0	3500		260	105	2800	1	10	600		
43		2.0	4.0	"	5400		590	210	3700	4	50	1750		
44		4.0	6.0	"	6900		400	300	2600	3	60	1950		
45		6.0	8.0	"	480		85	155	7200	3	210	80		
46		8.0	10.0	"	2450		220	1150	6000	5	10	820		
47		10.0	12.0	"	540									
48		12.0	13.9	1.9	270									
97100		13.9	15.9	2.0	920									
01		15.9	17.9	"	1650		490	150	95	2	25	200		
2		17.9	19.9	"	2550		410	34	80	1	25	100		
3		19.9	21.9	"	3000		360	34	50	1	35	520		
4		21.9	23.9	"	6100		510	35	26	1	85	2100		
5		23.9	25.9	"	3100		280	36	26	1	40	800		
6		25.9	27.9	"	5600		440	40	42	21	45	1250		
7		27.9	29.9	"	4000		330	160	210	1	35	3250		
8		29.9	31.9	"	1550		330	48	130	1	15	1150		
9		31.9	33.9	"	900		270	36	570	1	15	380		
10		33.9	36.1	2.2	740		260	30	1400	1	20	70		
11		36.1	38.1	2.0	450									
12		38.1	39.6	1.5	170									
13		39.6	41.6	2.0	100									
14		41.6	43.6	"	100									
15		43.6	45.3	1.7	70									
16		45.3	47.3	2.0	20									
17		47.3	49.3	"	14									
18		49.3	51.3	"	55									
19		51.3	53.3	"	65									
20		53.3	55.3	"	28									
21		55.3	57.3	"	10									
97122		57.3	60.07	2.77	44									

028390

Notes:— Sn by XRF B. Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT A
 ASSAY SUMMARY SHEET HOLE NO, MBD17

SAMPLE TYPE : DRILL CORE FROM 00 TO 60.07