

| SAMPLE NO. | SAMPLE NO   | FROM | TO   | INTER-<br>VAL | Sn    | Sn     | Cu  | Pb | Zn   | Ag | W  | As   | Check Sn | Bulked Assays |
|------------|-------------|------|------|---------------|-------|--------|-----|----|------|----|----|------|----------|---------------|
| SPLIT CORE | GROUND CORE | m    | m    | m             | SPLIT | GROUND |     |    |      |    |    |      |          |               |
| 97705      |             | 3.0  | 5.0  | 2.0           | 32    |        |     |    |      |    |    |      |          |               |
| 6          |             | 5.0  | 7.4  | 2.4           | 10    |        |     |    |      |    |    |      |          |               |
| 97315      |             | 7.4  | 9.4  | 2.0           | 30    |        |     |    |      |    |    |      |          |               |
| 16         |             | 9.4  | 11.4 | "             | 4650  |        | 160 | 40 | 6300 | 1  | 45 | 95   |          |               |
| 17         |             | 11.4 | 13.4 | "             | 1600  |        | 90  | ✓  | 1100 | 21 | 15 | 70   |          |               |
| 18         |             | 13.4 | 15.7 | 2.3           | 4400  |        | 55  | X  | 400  | 21 | 15 | 2400 |          |               |
| 19         |             | 15.7 | 17.7 | 2.0           | 120   |        |     |    |      |    |    |      |          |               |
| 20         |             | 23.3 | 25.3 | "             | 36    |        |     |    |      |    |    |      |          |               |
| 21         |             | 25.3 | 27.3 | "             | 50    |        |     |    |      |    |    |      |          |               |
| 22         |             | 27.3 | 30.2 | 2.9           | 28    |        |     |    |      |    |    |      |          |               |
| 23         |             | 34.4 | 36.4 | 2.0           | 14    |        |     |    |      |    |    |      |          |               |
| 24         |             | 36.4 | 38.4 | "             | 120   |        |     |    |      |    |    |      |          |               |
| 25         |             | 38.4 | 40.9 | 2.5           | 2500  |        |     |    |      |    |    |      |          |               |
| 26         |             | 40.9 | 42.9 | 2.0           | 26    |        |     |    |      |    |    |      |          |               |
| 97817      |             | 49.5 | 51.5 | 2.0           | 960   |        |     |    |      |    |    |      |          |               |
| 18         |             | 51.5 | 53.5 | "             | 1100  |        |     |    |      |    |    |      |          |               |
| 19         |             | 53.5 | 57.5 | "             | 270   |        |     |    |      |    |    |      |          |               |
| 20         |             | 57.4 | 59.2 | 1.8           | 490   |        |     |    |      |    |    |      | 540      | Pulp check    |
| 21         |             | 59.2 | 61.2 | 2.0           | 24    |        |     |    |      |    |    |      |          |               |
| 22         |             | 61.2 | 63.7 | 2.5           | 14    |        |     |    |      |    |    |      |          |               |
| 23         |             | 63.7 | 65.7 | 2.0           | 290   |        |     |    |      |    |    |      |          |               |

Notes: — Sn by XRF Bi Method.

X means less than detection limit

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT  
 ASSAY SUMMARY SHEET HOLE NO. MBD 21  
 SAMPLE TYPE: DRILL CORE FROM 3.0 TO 65.7