

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97345		1.0	3.0	3.0	230									
46		3.0	4.7	1.7	5500		230	35	440	21	30	330		
47		4.7	6.7	2.0	46									
48		6.7	8.7	"	60									
49		8.7	10.7	"	95									
50		10.7	11.6	.9	75									
51		11.6	13.6	2.0	1.21%		300	50	220	21	40	30		
52		13.6	15.6	"	5900		430	8	140	21	75	65		
53		15.6	17.6	"	6600		730	X	35	21	140	800		
54		17.6	19.6	"	6600			55	10	21	85	300		
55		19.6	21.6	"	2400		690	X	22	21	70	250		
56		21.6	23.6	"	2100		800	10	10	21	240	420		
57		23.6	25.6	"	740		950	X	16	21	30	20		
58		25.6	27.6	"	2250		1100	8	12	21	15	140		
59		27.6	29.6	"	2100		530	15	65	21	60	370		
60		29.6	31.6	"	120								120	Re check of check Ass.
61		31.6	32.7	1.1	110									
62		32.7	34.7	2.0	520									
63		34.7	36.7	"	2900									

Notes: - Sn by XRF B. Method.

X Means less than detection limit

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. MBD 22

SAMPLE TYPE: DRILL CORE FROM 1.0 TO 36.7

028413