

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97222		56.5	58.5	2.0	24									
23		58.5	61.4	2.9	24									
97212		78.5	80.5	2.0	3250									
13		80.5	82.5	"	600		170	30	440	2	10	260		
14		82.5	84.5	"	720		630	210	490	5	20	2250		
15		84.5	86.5	"	800		360	40	490	4	25	220		
16		86.5	88.5	"	920		410	40	780	4	110	410		
17		88.5	90.5	"	1150		460	150	740	4	10	420		
18		90.5	92.5	"	720		250	44	330	2	25	170		
19		92.5	94.5	"	2700		360	85	130	3	30	400		
220		94.5	97.3	2.8	1600		420	30	500	3	15	260		
21		97.3	99.3	2.0	90									

028421

Notes:— Sn by XRF B. Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT  
 ASSAY SUMMARY SHEET HOLE NO. MBD 24  
 SAMPLE TYPE : DRILL CORE FROM 56.5 TO 99.3