

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97224		64.0	66.0	2.0	290									
25		66.0	68.0	"	1550		240	46	240	2	20	660		
26		68.0	70.0	"	1500		250	70	230	1	20	65		
27		70.0	72.0	"	800		210	60	450	1	25	80		
28		72.0	74.0	"	2300		240	85	310	2	15	25		
29		74.0	76.0	"	3400		220	75	290	2	25	85		
230		76.0	78.0	"	1200		250	70	45	2	10	840		
31		78.0	80.0	"	2400		290	140	85	2	15	1050		
32		80.0	82.0	"	580		280	80	160	2	110	270		
33		82.0	84.0	"	2200		240	90	25	2	15	100		
34		84.0	86.0	"	960		190	120	700	4	20	20		
35		86.0	88.0	"	380		33	95	830	1	110	10		
36		88.0	88.7	0.7	320		42	130	480	1	20	10		
37		88.7	89.9	1.2	60									
38		89.9	91.9	2.0	170									
39		91.9	93.7	1.8	520									
240		93.7	95.7	2.0	190								160	Re check of check Sn
41		95.7	97.7	"	170									
42		97.7	98.9	1.2	960									
43		98.9	100.9	2.0	3450									
44		100.9	101.7	0.8	1050									
45		101.7	103.7	"	290									
46		103.7	104.7	"	350									
47		104.7	106.7	"	3300		250	20	50	1	15	250		
48		106.7	108.7	"	2650		280	55	50	2	40	180		
49		108.7	110.7	"	6000		320	140	65	3	30	560		
250		110.7	112.7	"	3300		340	150	210	3	20	150		
51		112.7	114.7	"	4400		430	250	160	4	110	2400		
52		114.7	116.7	"	1.62%		240	120	60	1	25	260		
53		116.7	118.7	"	1.67%		220	170	260	2	40	1850		

028495

Notes: - Sn by XRF Bi Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT  
 ASSAY SUMMARY SHEET HOLE NO. MBD 25 A  
 SAMPLE TYPE: DRILL CORE FROM 64.0 TO 118.7