

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97566		4.0	4.3	0.3	1050									
67		4.3	6.3	2.0	4450									
68		6.3	8.3	"	4900									
69		8.3	10.3	"	3100									
70		10.3	12.6	2.3	5800									
71		12.6	14.6	2.0	260									
72		14.6	16.6	"	4									
73		16.6	17.0	0.4	32									
74		17.0	19.0	2.0	50									
75		104.8	106.8	2.0	2550									
76		106.8	108.8	"	2350		470	60	55	2	25	340		
77		108.8	110.8	"	450		500	140	22	21	440	2250		
78		110.8	112.8	"	1100		440	5	16	21	35	320		
79		112.8	114.8	"	2450		320	13	16	21	55	640		
80		114.8	116.8	"	2000		350	17	22	21	30	260	960	Re-check of check Assay
81		116.8	118.8	"	2550		460	24	36	21	20	440		
82		118.8	120.8	"	840		950	4	20	21	10	120		
83		120.8	122.8	"	1150		550	10	20	21	15	280		
84		122.8	124.8	"	960		500	11	14	21	40	170		
85		124.8	126.8	"	2400		440	26	16	21	70	160		
86		126.8	128.8	"	4600		500	180	55	2	45	700		
87		128.8	130.0	1.2	3250		1500	1200	3100	16	60	1150		
88		130.0	132.7	2.7	2900									
89		132.7	133.7	1.0	2100									
590		133.7	135.7	2.0	430									
91		135.7	136.8	1.1	350									
92		136.8	138.8	2.0	1200									
93		138.8	140.8	"	520									
94		140.8	142.8	"	1050									

028443

Notes:— Sn by XRF B. Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
ASSAY SUMMARY SHEET HOLE NO. MBD 28 A
SAMPLE TYPE : DRILL CORE FROM 40 TO 142.8