

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97636		4.0	8.0	4.0	170									
38		8.0	10.0	2.0	1550									
39		10.0	12.0	"	540									
40		12.0	14.0	"	430								560	Pulp check Sn.
41		14.0	16.0	"	1200									
42		16.0	18.0	"	1700									
43		18.0	20.0	"	1550									
44		20.0	22.0	"	920									
45		22.0	24.0	"	3950									
46		24.0	26.0	"	680									
47		26.0	28.0	"	740									
48		28.0	30.0	"	400									
49		30.0	32.0	"	220									
650		32.0	34.0	"	95									
51		34.0	36.0	"	420									
52		36.0	38.0	"	260									
53		38.0	39.5	1.5	3200									
54		39.5	41.5	2.0	1000		1600	3800	840	3	210	700		
55		41.5	43.5	"	2850		220	260	140	1	25	230		
56		43.5	45.5	"	2400		250	100	110	2	30	310		
57		45.5	47.5	"	3850		250	90	50	2	10	330		
58		47.5	49.5	"	1350		610	620	5100	6	30	350		
59		49.5	51.5	"	1300		820	300	3000	8	50	170		
660		51.5	53.5	"	2600		270	110	160	1	35	230	2150	Pulp check
61		53.5	55.5	"	1500		230	260	640	2	10	320		
62		55.5	57.5	"	1650		270	480	340	2	10	2500		
63		57.5	59.5	"	600		95	640	860	3	10	470		
64		59.5	61.1	2.6	1600		200	2500	6500	7	10	320		
65		61.1	63.1	2.0	4.99%		930	350	100	1	210	1.41%		
66		63.1	65.1	2.0	2.68%		850	190	36	11	200	2.10%		

028453

Notes: - Sn by XRF B. Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT  
 ASSAY SUMMARY SHEET HOLE NO. MBD 29A  
 SAMPLE TYPE: DRILL CORE FROM 4.0 TO 65.1