

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97292		1.5	3.5	2.0	2350		470	65	70	2	30	360		
93		3.5	5.5	"	410		290	100	5200	2	20	210		
94		5.5	7.5	"	4300		310	55	910	1	25	260		
95		7.5	9.5	"	1.02%		1200	85	26	1	20	5300		
96		9.5	11.5	"	800		930	4	580	<1	210	540		
97		11.5	13.5	"	410		850	14	1600	<1	210	820		
98		13.5	15.5	"	1.42%		500	90	1500	<1	80	1350		
99		15.5	17.5	"	3350		540	440	9800	3	65	900		
976002		17.5	19.5	"	2600		920	740	250%	7	75	9160	2500	Recheck of check assay
01		19.5	21.5	"	5900		520	170	1.20%	1	55	800		
2		21.5	23.5	"	3950		430	100	7100	<1	40	600		
3		23.5	25.5	"	5100		410	120	4200	1	60	1750		
4		25.5	27.5	"	2850		430	40	2500	<1	10	320		
5		29.0	30.4	1.4	1000									
6		30.4	32.0	1.6	130									
7		32.0	34.0	2.0	85									
8		34.0	36.0	"	290									
9		36.0	37.8	1.8	350									
10		39.3	41.0	2.7	1000									
11		41.0	42.5	1.5	65									

028463

Notes: - Sn by XRF B. Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. MBD 31 A
 SAMPLE TYPE : DRILL CORE FROM 15 TO 42.5