

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97802		3.0	5.0	2.0	150									
3		5.0	7.0	"	14									
4		7.0	9.0	"	10									
5		9.0	11.0	"	10									
6		11.0	13.0	"	20									
7		13.0	15.0	"	18									
8		15.0	17.0	"	26									
9		17.0	19.0	"	28									
810		19.0	21.0	"	22									
11		21.0	23.0	"	30									
12		23.0	25.0	"	36									
13		25.0	27.0	"	90									
14		27.0	29.0	"	440									
15		29.0	31.0	"	180									
16		31.0	32.5	1.5	270									
97676		32.5	34.5	2.0	210									
77		34.5	36.5		130									
78		36.5	38.5	"	120									
79		38.5	40.5	"	80									
80		40.5	42.5	"	110								110	pulp check
81		42.5	44.5	"	1150									
82		44.5	46.5	"	300									
83		46.5	48.5	"	100									
84		48.5	50.5	"	34									
85		50.5	54.3	3.8	75									
86		54.3	56.3	2.0	100									
87		56.3	58.3	"	350									
88		58.3	60.3	"	820									
89		60.3	62.3	"	250									
90		62.3	63.3	"	620									

028488

Notes: — Sn by XRF Bi Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. MBD 35 A
 SAMPLE TYPE : DRILL CORE FROM 30 TO 63.3