

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97835		35.8	38.0	2.2	8400									
97824		174.5	176.5	2.0	65									
25		176.5	178.5	"	2100		260	65	630	21	35	60		
26		178.5	180.5	"	3750		330	20	120	21	25	85		
27		180.5	182.5	"	3150		310	65	190	21	20	160		
28		182.5	184.5	"	600		350	24	150	1	15	740		
29		184.5	186.5	"	460		300	26	160	21	210	4100		
30		186.5	188.5	"	500		330	15	80	21	25	2550		
31		188.5	190.5	"	1350		290	16	65	21	55	900		
32		190.5	192.5	"	1450		330	22	95	21	45	1200		
33		192.5	194.5	"	1450		300	40	150	1	10	75		
34		194.5	196.5	"	2600									

028496

Notes:— Sn by ARF Bi Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT  
 ASSAY SUMMARY SHEET HOLE NO. MBD 36  
 SAMPLE TYPE : DRILL CORE FROM 35.8 TO 196.5.