

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97836		71.0	72.3	1.3	3500									
37		106.1	108.1	2.0	260									
38		108.1	110.1	"	1150		290	80	96	2	20	32		
39		110.1	112.1	"	3450		440	100	190	3	30	600		
840		112.1	114.1	"	6100		360	55	170	<1	130	410	7000	Pulp check.
41		114.1	116.1	"	3800		570	60	220	1	45	700		
42		116.1	118.1	"	4650		400	20	290	1	30	920		
43		118.1	120.1	"	3350		430	50	200	<1	60	960		
44		120.1	122.1	"	3550		490	85	240	2	30	1400		
45		122.1	124.1	"	3500		590	110	390	2	20	1350		
46		124.1	125.8	1.7	2400		200	65	620	<1	20	220		
47		125.8	127.8	2.0	50									

028501

Notes:—

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. MBD 37
 SAMPLE TYPE : DRILL CORE FROM 71.0 TO 127.8