

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	As	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97871		20.4	22.5	2.1	1800									
72		40.3	42.3	2.0	320									
73		42.3	44.3	"	2000		300	55	48	1	25	160		
74		44.3	46.3	"	3700		190	46	36	<1	15	25		
75		46.3	48.3	"	2650		220	50	65	1	20	20		
76		48.3	50.3	"	4050		320	55	28	1	25	150		
77		50.3	52.3	"	4500		320	70	50	<1	30	140		
78		52.3	54.3	"	7400		340	100	45	1	30	140		
79		54.3	56.1	0.8	2700		450	65	95	1	25	360		
80		56.1	58.1	2.0	5200								0.28%	check assay

028511

Notes - Sn by XRF B. Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. MBD 39
 SAMPLE TYPE : DRILL CORE FROM 20.4 TO 58.1