

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
97946		49.0	51.7	2.7	2600									
97948		72.7	74.5	1.8	500									
97949		86.1	87.6	1.5	450									
97945		187.5	189.5	2.0	280									
96		189.5	191.5	"	1550									
97		191.5	193.5	"	1250									
98		193.5	195.5	"	320									
99		195.5	197.5	"	1850									
98000		197.5	199.5	"	1750								0.12%	check Assay
1		199.5	201.5	"	1350									
2		201.5	203.5	"	1800									
3		203.5	205.5	"	1150									
4		205.5	207.5	"	3400									
5		207.5	209.5	"	540									
6		209.5	211.5	"	1200									
7		211.5	213.5	"	920									
8		213.5	215.0	1.5	1750									
9		215.0	217.0	2.0	3950									

028527

Notes: - Sn by XRF B₁ Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET. HOLE NO. MBD 42
 SAMPLE TYPE : DRILL CORE FROM 49.0 TO 217.0