

SAMPLE NO.	SAMPLE NO	FROM	TO	INTER-VAL	Sn	Sn	Cu	Pb	Zn	Ag	W	Au	Check Sn	Bulked Assays
SPLIT CORE	GROUND CORE	m	m	m	SPLIT	GROUND								
98051		25.4	27.4	2.0	18									
52		27.5	29.5	"	200									
53		29.5	31.5	"	140									
54		31.5	33.5	"	60									
55		33.5	35.5	"	46									
56		35.7	37.5	1.8	80									
57		37.5	39.5	2.0	110									
58		39.5	41.5	"	75									
59		41.5	43.5	"	70									
60		43.5	45.5	"	80								210	check Assay
61		45.5	47.5	"	75									
62		47.5	49.5	"	85									
63		49.5	51.5	"	160									
64		51.5	53.0	1.5	250									
65		53.0	55.0	2.0	85									
66		149.9	151.0	1.1	4600									
67		154.0	156.0	2.0	130									
68		156.0	156.5	0.5	6.38%									
69		156.5	158.5	2.0	240									
70		237.2	237.6	0.4	1.44%									

028544

Notes: — Sn by XRF B. Method.

METALS EXPLORATION LTD - MT BISCHOFF TIN PROSPECT
 ASSAY SUMMARY SHEET HOLE NO. MBD 45
 SAMPLE TYPE: DRILL CORE FROM 25.4 TO 237.6