

DRILL ADVANCE				LITHOLOGY						
DEPTH	DRILL ADVANCE INTERVAL	CORE RECOVERY	PERCENT RECOVERY	INTERVAL	DESCRIPTION	ALTERATION	GRAPHIC LOG	STRUCTURE	MINERALISATION	VISUAL PERCENTAGE MINERALISATION
15.7	0.8	0.65	81%	16						
16.5	1.0	1.0	100%	17						
17.5	0.9	0.8	88%	17.5	Massive to thinly bedded chloritic siltstones to fine sandstones. Where laminate bedding occurs there is evidence of deformation. Core has a distinct green grey colour and is fractured and broken. Numerous thin (1-2 mm) quartz veins cut the core, and much of the sequence shows brecciation.	Minor limonite along joints and fracture zones. Chlorite development	18.0 Bedding to core axis: 38° 21.7 Bedding to core axis: 25° 21.8 20 mm thick white quartz vein. 23.7 Bedding to core axis: 10° 25.8 Bedding to core axis: 25° 26.2 5 mm quartz vein: 25° 27.0 quartz vein: 55°	21.7 20 mm zone of pyrite and arsenopyrite.	5%	
18.4	1.1	0.88	77%	18						
19.3	0.7	0.7	100%	19						
20.2	0.7	0.7	100%	20						
20.9	1.0	1.0	100%	21						
21.9	0.8	0.8	100%	22						
22.7	0.7	0.7	100%	23						
23.4	0.6	0.6	100%	24						
24.0	0.9	0.6	67%	25						
24.9	1.0	0.9	90%	26						
25.9	0.7	0.7	100%	27						
26.6	1.4	1.4	100%	28						
28.0	2.7	1.9	70%	28.3	thin brecciated horizon. Clasts approx 5mm.				minor pyrite in vein	5%
				29.0						

SCALE 1:100 (1cm = 1 m)

COMSTAFF PROPRIETARY LIMITED

DRILLHOLE LOG FOR DDH RBE 7

LOGGED BY _____ FROM 15 TO 30

DATE 24/5/80

PAGE 2 OF 13