

81-1558

968001

MICROFILMED

of M.	A.O.	C.G.	E.O.	D.S.M.
Received	11 SEP 1981			E.S.T.
Answered				
DEPT. OF THE ARMY				
REP. No.				

EXPLORATION LICENCE NO. 18/76.

SIX MONTHLY REPORT

FOR

PERIOD FROM 5/2/81 TO 4/8/81

AMG REFERENCE POINTS ADDED

TABLE OF CONTENTS

1. INTRODUCTION

2. OBJECTIVES OF THE EXPLORATION AND REASONS FOR SELECTING THE LICENCE AREA

3. DETAILS AND RESULTS OF THE EXPLORATION, SURVEYS AND INVESTIGATIONS.
 - 3.1 Searching for Quartzite Outcrops.
 - 3.2 Sampling of Outcrops and Analyses of Samples.
 - 3.3 Investigation of all Exploration, Surveys , etc.
 - 3.4 Results of the Investigation.

4. PROPOSED TESTING OF THE SELECTED AREAS

5. PROGRAMME

APPENDICES

- PLATE 1 : Part of B.H.P.'s Map showing E.L. 18/76.
- PLATE 2 : M.H.A.'s Plan showing E.L. 18/76 and the Quartzite Areas and Outcrops and Outcrops sampled.
- TABLE 2 : M.H.A.'s Outcrops and Areas of Quartzite.
- TABLE 5 : Results of Analyses of Samples from Drill Holes by B.H.P. on E.L. 18/76.

LIST OF PLATES

- PLATE 1 : Part of B.H.P.'s Map showing E.L. 18/76.
- PLATE 2 : M.H.A.'s Plan showing E.L. 18/76 and the Quartzite Areas and Outcrops and Outcrops sampled.

LIST OF TABLES

- TABLE 1 : B.H.P.'s testing.
- TABLE 2 : M.H.A.'s Outcrops and areas of Quartzite.
- TABLE 3 : Correlation of B.H.P.'s Testing Places and M.H.A.'s Outcrops.
- TABLE 4 : Analyses of Silica Samples (M. Kit's).
- TABLE 5 : Results of Analyses of Samples from Drill Holes by B.H.P. on E.L. 18/76.

SIX MONTHLY REPORT ON EXPLORATION LICENCE NO. 18/76 IN
NORTH WESTERN TASMANIA

1. INTRODUCTION

This report covers the period of the Licence from 5th February 1981 to 4th August 1981. A Quarterly Report for the second half of the period has already been prepared for the Department of Mines.

Much of the information that will be given in this Report was included in the following report :-

Report on Exploration and Investigation on E.L. 18/76
to date by P.B. Nye 2/6/81.

Moreover there is considerable information in the Report that will not be in this Six Monthly Report. A copy of the above Report will be attached to this Report. Many references will be made to the Report of 2/6/81 and particularly to the maps, plans and tables in it.

2. OBJECTIVES OF THE EXPLORATION AND REASONS FOR SELECTING THE LICENCE AREA

Mineral Holdings found some quartzites on E.L. 43/70 and kept extending its area to the north. It subsequently found that the quartzites corresponded to the Jacob Ortho quartzite and the Detention Sub group of the Rocky Cape Group of Proterozoic rock as shown on the Table Cape and Burnie sheets of the 1 mile geological series. The B.H.P. company obtained the area of E.L. 18/76 and tested it but eventually (in 1978) transferred it to Mineral Holdings.

The quartzites were required for their silicon content which is used amongst other uses in the manufacture of alloys with metals and also in the manufacture of metallic silicon.

3. DETAILS AND RESULTS OF THE EXPLORATION, SURVEYS AND INVESTIGATION.

3.1 SEARCHING FOR QUARTZITE OUTCROPS

The searching was done by Mr. K. Pinner examining the Licence area for outcrops of quartzites, and also seeking to find the drill holes and the lines of bulk surface chip samples taken by the B.H.P. company.

B.H.P. showed their drill holes and surface chip samples on a map to a scale of 1:31680 and representing an enlargement of the Table Cape Geological Sheet of the 1 mile series (1:63360). The map has the same scale (1:31680) as the County Land Charts of the Lands Department. The Department of Mines uses the County Land Chart (Wellington 3C) on which to mark the mining tenements (including the Exploration Licences) to form their mineral chart.

Mineral Holdings located 16 outcrops and areas of outcrops and marked them on a map based on the Wellington 3C Land Chart and that map shows the boundaries of the

Licence. A photocopy of B.H.P.'s map is shown as Plate 1 of the report of 2/6/81. A revised copy of M.H.A.'s map is shown as Plate 2 in the report of 2/6/81 and a copy is attached to this six-monthly report.

As stated above, Mineral Holdings shows the 16 outcrops or areas of outcrops on their map and the outcrops are numbered from 1 to 16. It shows also the outcrops and areas of outcrops from which samples were taken by placing the sample number (1 to 7) alongside the outcrops.

3.2 SAMPLING OF OUTCROPS AND ANALYSES OF SAMPLES

Surface chip samples were taken from 6 of the 16 outcrops or areas of outcrops shown on the map of Mineral Holdings. (Plate 2).

Some details of the quartzite areas and of the places sampled are given in Table 2 of the report of 2/6/81 and a copy is reproduced below.

Table 2
Outcrops of Quartzite

Number of Outcrop	Length Fees	Width Fees	Strike °	Dip °	Number of sample for Assay	Notes
1			180			Along ridge
3	100	50	180			
4		30	195		1	
5		75	188			
6						Outcrops for low grade iron-stained quartzite
7		66			2	Very soft material
8	100				3	Iron-stained
9		40	220	Vert		
10		30	185		4	Pink-stained
11			190			Small outcrop
12	50	100	225	30 West		
13	100	100	235			Iron-stained
14	300	60	40	45	5	Base of outcrop about 200ft. wide. Rises about 150ft. above river level
15						Scattered outcrop extend over 0.5 miles to north-east of Area 14.
16		40	Vert		(6 (7	Outcrop on western side of river and extends to 100ft. above it. Sample 6 is on northern side and outcrop and 7 on southern side.

The results of the analyses of the seven samples taken by Mineral Holdings are given in Table 4 of the report of 2/6/81. The table is repeated below.

Table 4
E.L. 18/76
Analyses of Silica Samples (M.H.A.'s)

Reg. No.	Sample No.	Analyses					M.H.A. Outcrops	
		SiO ₂ %	Fe %	Al ₂ O ₃ %	Ti %	Ca %		
810,095	1	99.3	0.24	0.10	0.62	0.02	Outcrop Area 4	
096	2	99.6	0.12	0.04	0.04	0.01	" "	7
097	3	98.9	0.46	0.10	0.04	0.01	" "	8
099	5	99.7	0.19	0.02	0.01	0.01	" "	14
100	6	99.4	0.25	0.06	0.04	0.01	" "	16
101	7	99.4	0.26	0.06	0.02	<0.01	" "	16

3.3 INVESTIGATION OF ALL EXPLORATION

This included the consideration of the drilling and surface sampling by the B.H.P. company and the subsequent exploration and surface sampling by Mineral Holdings Australia. The results were described in the following report :

Report of Exploration and Investigation on E.L. 18/76 to Date,
P.B. Nye, 2nd June 1981.

A copy of the above report was forwarded to the Department of Mines of Tasmania on 11th June, 1981 and one is attached to this Report. The objective of the investigation was to select two areas for further detailed testing.

3.4 RESULTS OF THE INVESTIGATION

The results were described in the report of 2/6/81 and the following description is taken from that report.

Selection of Best Holes and Areas for Further Testing:

The selection of areas for further testing depends upon many factors including silica content, content impurities, hardness of material, suitability for open cutting, etc. Some of these factors have been discussed above.

Information on other factors such as hardness of quartzite and suitability of site for open cutting have been obtained from Mr. K. Pinner. In regards to hardness, Pinner stated that the hardest material was near M.H.A.'s outcrops 3, 5, 12, 13 and 15. Outcrops (3) and (5) may be parts of the same zone of quartzite. Similarly outcrops (12) and (13) may be parts of a zone. Outcrop 15 is in one and the same zone of quartzite between outcrops (7) and (14).

In regard to suitability of area for open cutting, Pinner states that outcrop (15) and area (16) which includes samples 6 and 7 are the best.

It will be noted that outcrop (or area) 15 is the only one that contains hard material and is in a suitable place for open cut operations.

In regard to the silica and alumina contents of the four zones or areas referred to above, the position may be summarised as follows:-

Area (3) - (5)

This area contains drill holes SC40,41 and 42 that have average silica contents of 98.57, 92.6 and 98.37 percent respectively and average alumina contents of 0.87, 0.40 and 0.2 per cent respectively. The silica content is low and the alumina content high.

Area (12) - (13)

This area contains drill holes SC27 and 28 that have average silica contents of 99.11 and 99.35 percent respectively and average alumina contents of 0.13 and 0.05 percent respectively.

Area (15)

This area contains drill holes SC29,30,31 and 35 but no results are given for hole 29. Holes 30,31 and 35 contain average silica contents of 99.35, 99.4 and 99.4 percent respectively and alumina contents of 0.075, 0.05 and 0.05 percent respectively.

It is situated between M.H.A. samples (2) and (5) which have silica contents of 99.6 and 99.7 percent respectively and alumina content of 0.1 and 0.1 percent respectively.

Area 16

This area contains M.H.A.'s samples (6) and (7) that have silica contents of 99.4 percent and alumina contents of 0.01 and <0.01 percent respectively.

In the above summary of information, it will be noted that Area (15) and Area (16) are the only two considered to be generally suitable for open cut operations. Of these two, however, Area (15) contains hard quartzite material.

Further, in Area 15 in M.H.A. samples show the highest silica contents (99.6 and 99.7%) and the drill holes SC30,31 and 35 have silica contents of 99.30, 99.4 and 99.4% respectively. The alumina contents of Area 15 in the drill holes SC30, 31 and 35 are 0.075, 0.05 and 0.05 percent respectively. M.H.A.'s samples (2) and (5) are also high in silica (99.6 and 99.7% respectively) and low in alumina (0.1 and 0.1 respectively).

In area 16, the only testing has been M.H.A. samples (6) and (7), but they indicate that the silica content is high (99.4%) and the alumina content (0.01 and <0.01 is low).

It would appear therefore that Area (15) is the best for testing, and that some further sampling is justified on Area (16).

4. PROPOSED TESTING OF THE SELECTED AREAS

As a result of the investigation as described in the previous section of this report, two areas (15 and 16) were selected for further examination and for testing by drilling.

Discussions were started with Longworth and McKenzie (the Company was drilling at Irishtown on E.L. 10/79 of Mineral Holdings) for that company to conduct the examination and drilling of the two selected areas (and also to carry out work on E.L. 29/80). Unfortunately the company closed its season after the completion of the Irishtown drilling.

In its letter of 26/6/81, Longworth & McKenzie informed Mineral Holdings that it was prepared to do the work on E.L. 18/76 and E.L. 29/80. That company desired information and discussions with Messrs. N.M. Thomas and P.B. Nye so that it could form a programme and prepare a budget estimate and decide on timing for the work.

Mineral Holdings sent a copy of the report of 2/6/81 to the company and will be having discussions with its representatives.

Mineral Holdings has already furnished information on E.L. 29/80 to Longworth & McKenzie about and will be sending more and holding discussions with the company. The discussion had to be postponed until after the return of the Managing Director of M.H.A..


5. PROGRAMME

After the completion of the drilling and examination of the results, a further programme will be prepared and exploration and testing will be conducted in accordance with that programme. The following programme was included in the application of 31 July 1981 for an extension beyond 4 August 1981.

The programme is based on the one for the current period and will be:

1. hold discussions with Longworth & McKenzie Co. to finalise arrangements for the Company to conduct geological surveys of selected area;
2. the Longworth and McKenzie Co. to investigate the two selected areas and decide on the positions and the number of drill holes to be put down;
3. to conduct the drilling of percussion holes by the Longworth & McKenzie Co.;
4. to conduct further testing on the selected areas based on the results of the drilling.


The details of the finance in the above will be forwarded as soon as they are finalised by the Longworth and McKenzie Co. and supplied to Mineral Holdings.


N.M. THOMAS
MINERAL HOLDINGS
AUSTRALIA PTY. LTD.

145°35'E

PLATE I

AMG REFERENCE POINTS ADDED



Scale 1:31,680 (1 INCH = 40 CHAINS)

5 cm

Boundary of Jacob Quartzite

E.L. 18/76 E.L. Boundary

Percussion Drill Hole Location

PART OF B.H.P.'S MAP

Bulk chip sample traverse location

(SHOWING E.L. 18/76.)

E.L. 18/76

- 1. QUARTZITE OUTCROP.
- NUMBER OF OUTCROP.
- ▲ " " SAMPLE
- +— RAILWAY


5 cm

SCALE

1 INCH = 0.5 MILE.

BASS STRAIT.

JACOBS BOAT HARBOUR.



Based on surveys
 by R. Penner
 P.P. 18/80
 1/8/80
 10/5/81

TABLE 1

B.H.P.'s Testing

Bulk Chip Samplings			Percussion Holes	
	Number of places	Number given to each sampling	Holes	Number given to each hole
Northern	5	5503, 5440 5439, 5438	7	SC42, SC41, SC40 SC36, SC37, SC39 SC38
Central	5	5505, 5504 5478, 5477 5476	7	SC29, SC31, SC30 SC35, SC33, SC32 SC34, SC20, SC25 SC27, SC28
Southern	0	-	3	SC22, SC23, SC24

Table 3

B.H.P.	M.H.A.'s	B.H.P.'s	
Area of Jacob Quartzite	Outcrop Numbers	Chip Sample Number	Percussion Hole Number
Northern	1	None	None
	2	5440	
	3	5439	SC42
	4	5563	
	5	5438	SC36, 37, 40, 41
	6	-	SC38, 39
Central	7	-	SC29, 20, 31
	8	5505	SC25, 26
	9	-	
	10	5478	
	11	5504	SC25 and 26
	12	-	-
	13	5476	SC27 and 28
	14	5477	-
	15	-	SC32, 33, 34, 35
	Southern	16	-
-		-	SC22, 23, 24

RESULTS OF ANALYSES

OF

SAMPLES FROM DRILL HOLES BY B.H.P. ON E.L. 18/76

<u>Sample Marked</u>	<u>SiO₂</u>	<u>Fe₂O₃</u>	<u>Al₂O₃</u>
SC22 3-6m	98.9	0.19	0.10
SC22 6-12m	98.8	0.25	0.15
SC22 12-15m	98.9	0.25	0.25
SC23 0-6m	98.7	0.25	0.15
SC23 6-12m	97.0	0.35	1.3
SC24 0-6m	98.8	0.20	0.05
SC24 6-12m	99.3	0.15	0.05
SC25 0-6m	99.4	0.10	0.05
SC25 6-12m	99.5	0.15	0.05
SC25 12-18m	99.6	0.15	0.05
SC25 18-21m	99.0	0.20	0.10
SC26 0-6m	99.2	0.05	0.05
SC26 6-12m	99.3	0.10	0.05
SC26 12-15m	99.3	0.15	0.05
SC27 0-3m	99.4	0.10	0.10
SC27 3-9m	99.0	0.15	0.15
SC28 0-6m	99.3	0.15	0.05
SC28 6-12m	99.2	0.15	0.05
SC30 0-6m	99.3	0.10	0.10
SC30 6-12m	99.4	0.05	0.05
SC31 3-6m	99.4	0.30	0.05
SC32 0-3m	99.3	0.30	0.10
SC32 12-15m	99.1	0.25	0.15
SC32 18-21m	98.9	0.25	0.15
SC33 6-9m	99.2	0.45	0.10
SC33 9-15m	99.3	0.20	0.05
SC33 18-21m	98.1	0.20	0.70
SC34 3-9m	99.1	0.25	0.10
SC34 9-15m	99.4	0.25	0.05
SC35 0-3m	99.4	0.20	0.05
SC36 0-6m	99.1	0.35	0.20
SC36 6-12m	98.8	0.25	0.25
SC36 12-18m	95.6	0.35	2.0
SC39 3-6m	99.0	0.25	0.10
SC39 9-12m	94.5	0.30	2.7
SC40 0-6m	98.3	0.30	0.55
SC40 9-12m	98.7	0.25	0.15
SC41 3-6m	95.7	0.35	2.3
SC41 6-12m	91.1	0.75	4.8
SC42 3-6m	98.9	0.15	0.10
SC42 6-12m	98.1	0.20	0.25
SC42 12-18m	97.1	0.45	0.95

Introduction

This licence was taken over by Mineral Holdings Australia (MHA) from B.H.P. when the latter company had completed its investigations the B.H.P. Company prepared a map showing on the part dealing with the above Licence area the following -

1. the geology as shown on the 1 mile Geological 1 mile sheets Table Cape and Burnie and showing the Jacob Orthoquartzite in which the quartzites being investigated are present.
2. the traverses along which bulk surface chip samples were taken.
3. the positions of the percussion drill holes that were put down.

The map does not show the quartzite outcrops and the areas occupied by the quartzite, and M.H.A.'s first exploration was therefore a search to locate the main outcrops and areas containing scattered outcrops. At the same time, some preliminary chip samples were taken from some of the outcrops. The outcrops and the places where samples were taken were marked on a map. The searching was completed and 16 outcrops or areas of outcrop were marked on the map. They agree generally with the places where B.H.P. took bulk surface chip samples and drilled percussion holes.

B.H.P.'s Testing

The B.H.P. Company took 11 bulk surface chip samples and drilled 21 percussion holes on the Licence area; there was an additional chip sample (5444) to the north-east of the Licence area. There are three large tracts of Jacob Quartzite on the Licence area.

The quartzite tracts being investigated occur in Jacob Quartzite, and the distribution of chip samples and drill holes in the three tracts is shown in Table 1. For descriptive purposes, the three tracts will be termed the Northern, Central and Southern.

Table 1
B.H.P.'s Testing

	Bulk Chip Samplings		Percussion Holes	
	Number of places	Number given to each sampling	Holes	Number given to each hole
Northern	5	5503, 5440 5439, 5438	7	SC42, SC41, SC40 SC36, SC37, SC39 SC38
Central	5	5505, 5504 5478, 5477 5476	7	SC29, SC31, SC30 SC35, SC33, SC32 SC34, SC20, SC25 SC27, SC28
Southern	0	-	3	SC22, SC23, SC24

The positions of each sampling and drill hole are shown on Plate 1 (attached). The analyses of samples from the drill holes are shown on Table 5 (attached).

Outcrops of Quartzite Located by M.H.A.

The outcrops of quartzites located by M.H.A. have been numbered from (1) to (16), and the samples taken have been numbered from (1) to (7) and the positions of both are shown on Plate 2 (attached).

Some information about the outcrops are given in the attached table (Table 2).

Correlation of B.H.P.'s Testing Places and M.H.A.'s Outcrops

The correlation between M.H.A.'s quartzite outcrops and B.H.P.'s testing places is given in the following table (Table 3).

Table 3

B.H.P.	M.H.A.'s	B.H.P.'s	
Area of Jacob Quartzite	Outcrop Numbers	Chip Sample Number	Percussion Hole Number
Northern	1	None	None
	2	5440	
	3	5439	SC42
	4	5563	
	5	5438	SC36, 37, 40, 41
	6	-	SC38, 39
Central	7	-	SC29, 20, 31
	8	5505	SC25, 26
	9	-	
	10	5478	
	11	5504	SC25 and 26
	12	-	-
	13	5476	SC27 and 28
	14	5477	-
	15	-	SC32, 33, 34, 35
Southern	16	-	-
	-	-	SC22, 23, 24

Analyses of Samples

Some of the details of the samples taken by M.H.A. are shown in Table 2 (attached).

The details of the analyses by the Department of Mines laboratory in Launceston are given in the following table (Table 4).

Table 4

E.L. 18/76

Analyses of Silica Samples (M.H.A.'s)

Reg. No.	Sample No.	Analyses					MHA Outcrops	
		SiO ₂ %	Fe %	Al ₂ O ₃ %	Ti %	Ca %		
810,095	1	99.3	0.24	0.10	0.62	0.02	Outcrop Area	4
096	2	99.6	0.12	0.04	0.04	0.01	"	" 7
097	3	98.9	0.46	0.10	0.04	0.01	"	" 8
098	4	99.5	0.20	0.06	0.02	0.01	"	" 10
099	5	99.7	0.19	0.02	0.01	0.01	"	" 14
100	6	99.4	0.25	0.06	0.04	0.01	"	" 16
101	7	99.4	0.26	0.06	0.02	<0.01	"	" 16

Silica Content of Samples

The attached Table 5 giving the analyses of the B.H.P. drill hole samples shows that for the holes between 24 and 32 inclusive, excepting the top sample in hole 4 and the lowest samples in hole 32, the silica content is 99.0 percent or more. The average of the 17 samples is 99.2 percent, the highest content being 99.6 percent in hole 25. With the exception of the upper sample in hole 22, the holes are all situated on the Central area.

The remaining holes on the Central area (33, 34 and 35) could be included because of the six samples in them only one has a silica content below 99.0, and the average of the six is 99.1 percent.

Of the seven chip samples taken by M.H.A., only one (No. 3) had a silica sample less than 99.0, and its silica content was 98.9. The average of the six samples is 99.4. Of M.H.A.'s seven samples one is in the Northern, four in the Central area and two in the Southern area.

In the Southern area, there are three B.H.P. Holes with a total of 4 samples and all have a silica content below 99.0 percent. The two samples of M.H.A. in the same area have contents of 99.4 percent.

Selection of Best Holes and Areas for Further Testing

The selection of areas for further testing depends upon many factors including silica content, content impurities, hardness of material, suitability for open cutting, etc. Some of these factors have been discussed above.

Information on other factors such as hardness of quartzite and suitability of site for open cutting have been obtained from Mr. K. Pinner. In regards to hardness, Pinner stated that the hardest material was near M.H.A.'s outcrops 3, 5, 12, 13 and 15. Outcrops (3) and (5) may be parts of the same zone of quartzite. Similarly outcrops (12) and (13) may be parts of a zone. Outcrop (15) is in one and the same zone of quartzite between outcrops (7) and (14).

In regard to suitability of area for open cutting, Pinner states that outcrop (15) and area (16) which includes samples 6 and 7 are the best.

It will be noted that outcrop (or area) 15 is the only one that contains hard material and is in a suitable place for open cut operations.

In regard to the silica and alumina contents of the four zones or areas referred to above, the position may be summarised as follows :-

Area (3) - (5)

This area contains drill holes SC40, 41 and 42 that have average silica contents of 98.57, 92.6 and 98.37 percent respectively and average alumina contents of 0.87, 40 and 0.2 percent respectively. The silica content is low and the alumina content high.

Area (12) - (13)

This area contains drill holes SC27 and 28 that have average silica contents of 99.11 and 99.35 percent respectively and average alumina contents of 0.13 and 0.05 percent respectively.

Area (15)

This area contains drill holes SC29, 30, 31 and 35 but no results are given for hole 29. Holes 30, 31 and 35 contain average silica contents of 99.35, 99.4 and 99.4 percent respectively and alumina contents of 0.075, 0.05 and 0.05 percent respectively.

It is situated between M.H.A. samples (2) and (5) which have silica contents of 99.6 and 99.7 percent respectively and alumina content, of 0.1 and 0.1 percent respectively.

Area (16)

This area contains M.H.A.'s samples (6) and (7) that have silica contents of 99.4 percent and alumina contents of 0.01 and <0.01 percent respectively.

In the above summary of information, it will be noted that Area (15) and Area (16) are the only two considered to be generally suitable for open cut operations. Of these two, however, Area (15) contains hard quartzite material.

Further, in Area 15, M.H.A. samples show the highest silica contents (99.6 and 99.7%) and the drill holes SC30, 31 and 35 have silica contents of 99.30, 99.4 and 99.4% respectively. The alumina contents of Area 15 in the drill holes SC30, 31 and 35 are 0.075, 0.05 and 0.05 percent respectively. M.H.A.'s samples (2) and (5) are also high in silica (99.6 and 99.7% respectively) and low in alumina (0.1 and 0.1 respectively).

In area 16, the only testing has been M.H.A. samples (6) and (7), but they indicate that the silica content is high (99.4%) and the alumina content (0.01 and <0.01 is low).

It would appear therefore that Area (15) is the best for testing, and that some further sampling is justified on Area (16).



P.B. NYE

Melbourne
2nd June, 1981

RESULTS OF ANALYSES

968018

OF

SAMPLES FROM DRILL HOLES BY B.H.P. ON E.L. 18/76

<u>Sample Marked</u>	<u>SiO₂</u>	<u>Fe₂O₃</u>	<u>Al₂O₃</u>
SC22 3-6m	98.9	0.19	0.10
SC22 6-12m	98.8	0.25	0.15
SC22 12-15m	98.9	0.25	0.25
SC23 0-6m	98.7	0.25	0.15
SC23 6-12m	97.0	0.35	1.3
SC24 0-6m	98.8	0.20	0.05
SC24 6-12m	99.3	0.15	0.05
SC25 0-6m	99.4	0.10	0.05
SC25 6-12m	99.5	0.15	0.05
SC25 12-18m	99.6	0.15	0.05
SC25 18-21m	99.0	0.20	0.10
SC26 0-6m	99.2	0.05	0.05
SC26 6-12m	99.3	0.10	0.05
SC26 12-15m	99.3	0.15	0.05
SC27 0-3m	99.4	0.10	0.10
SC27 3-9m	99.0	0.15	0.15
SC28 0-6m	99.3	0.15	0.05
SC28 6-12m	99.2	0.15	0.05
SC30 0-6m	99.3	0.10	0.10
SC30 6-12m	99.4	0.05	0.05
SC31 3-6m	99.4	0.30	0.05
SC32 0-3m	99.3	0.30	0.10
SC32 12-15m	99.1	0.25	0.15
SC32 18-21m	98.9	0.25	0.15
SC33 6-9m	99.2	0.45	0.10
SC33 9-15m	99.3	0.20	0.05
SC33 18-21m	98.1	0.20	0.70
SC34 3-9m	99.1	0.25	0.10
SC34 9-15m	99.4	0.25	0.05
SC35 0-3m	99.4	0.20	0.05
SC36 0-6m	99.1	0.35	0.20
SC36 6-12m	98.8	0.25	0.25
SC36 12-18m	95.6	0.35	2.0
SC39 3-6m	99.0	0.25	0.10
SC39 9-12m	94.5	0.30	2.7
SC40 0-6m	98.3	0.30	0.55
SC40 9-12m	98.7	0.25	0.15
SC41 3-6m	95.7	0.35	2.3
SC41 6-12m	91.1	0.75	4.8
SC42 3-6m	98.9	0.15	0.10
SC42 6-12m	98.1	0.20	0.25
SC42 12-18m	97.1	0.45	0.95