

<u>Hole</u> <u>No.</u>	<u>Water</u> <u>(ft.)</u>	<u>Interval</u> <u>(ft.)</u>	<u>OMAG</u> <u>No.</u>	<u>Register</u> <u>No.</u>	<u>N</u> <u>(%)</u>	<u>H. Assay (g/t)</u>			<u>Remarks</u>
						<u>Sn</u>	<u>Ti.</u>	<u>Zr</u>	
42	95	0 - 3.5	324	664129	0.06	42	13	24	
		3.5 - 7	325	30	0.09	110	3	13	
		7 - 9.5	326	1	0.11	40	10	19	
43	82	0 - 3	327	664132	0.04	4	2	2	
44	72	0 - 2.5	328	664133	0.06	23	4	11	
45	94	0 - 3	329	664134	0.09	51	5	7	
		3 - 5.5	330	664165	0.05	24	2	4	
		5.5 - 7.5	331	6	0.05	42	7	19	
		7.5 - 9	332	7	0.11	30	3	7	
46	104	0 - 1.5	333	664168	0.25	13	11	17	
		1.5 - 3	334	9	0.05	2	2	3	
		3 - 5	335	70	0.13	T	N	2	
		5 - 7	336	1	0.07	2	2	3	
47	110	0 - 1.5	337	664172	0.19	47	17	40	
		1.5 -	338	3					
		- 5	339	4					
		5 - 10	340	5	0.13	8	6	8	Clays not Treated
48	113	0 - 3.5	341	664176	0.21	116	17	38	
		3.5 - 6	342	7	0.08	19	6	14	
		6 - 8	343	8	0.48	1	9	13	
		8 - 10.5	344	9	0.17	T	4	13	
		10.5 - 12.5	345	80	0.22	1	9	10	