

From	To	Interl (m)	Core Rec'd	% Rec	Sample No.	Compos No.	Assays								Weighted Assa
							Ag	Bi	As	Cd	Ta	Fe%	Co	Cr	
0.00	3.60	3.60			722	f	<1	<4	75	<1	<10	1.65	35	44	
3.60	4.80	1.20			723	s	<1	<4	65	<1	<10	6.5	8	90	
4.80	8.30	3.50			724	s	<1	<4	42	<1	<10	2.1	16	95	
8.30	15.60	7.30			725	f	<1	<4	8	<1	<10	2.95	22	24	
15.60	18.40	2.80		100	726	f	<1	<4	26	<1	<10	2.76	28	60	
18.40	21.00	2.60		100	727	f	<1	<4	20	<1	<10	1.90	24	40	
21.00	27.00	6.00		100	728	f	<1	<4	10	<1	<10	2.0	42	55	
27.00	28.60	1.60		100	729	s	<1	<4	10	<1	10	1.55	6	105	
28.60	34.00	5.40		100	730	f	<1	<4	48	<1	10	3.5	22	40	
34.00	36.00	2.00		100	731	e	<1	8	18	<1	<10	1.75	6	85	
36.00	43.80	7.80		100	732	f	<1	<4	16	<1	<10	2.9	26	50	
43.80	44.60	0.80		100	733	s	<1	6	8	<1	<10	9.4	14	90	
44.60	50.00	5.40			734	f	<1	<4	24	<1	<10	3.7	26	48	
50.00	57.00	7.00		100	735	f	<1	<4	32	<1	<10	3.2	20	32	
57.00	65.00	8.00			736	f	<1	<4	26	<1	10	2.0	16	40	
65.00	73.00	8.00			737	f	<1	<4	48	<1	<10	1.85	22	44	
73.00	75.00	2.00			738	s	<1	6	28	<1	<10	1.05	18	80	
75.00	81.00	6.00		100	739	f	<1	<4	46	<1	<10	1.85	28	32	
81.00	85.50	4.50			740	s	<1	<4	32	<1	<10	1.75	6	75	
85.50	90.00	4.50		100	741	f	<1	<4	40	<1	<10	2.2	24	50	
90.00	95.00	5.00		100	742	f	<1	<4	24	<1	10	1.85	22	36	
95.00	101.00	6.00		100	743	f	1	<4	32	<1	10	2.3	22	28	
101.00	103.00	2.00		100	744	s	<1	4	36	<1	<10	1.95	14	31	
103.00	110.00	7.00		100	745	f	<1	<4	44	<1	10	1.85	28	32	
110.00	120.00	10.00		100	746	f	1	<4	75	<1	<10	1.95	36	32	
120.00	127.00	7.00			747	f	1	<4	34	<1	<10	2.2	32	36	
127.00	129.00	2.00			748	s	<1	<4	26	2	<10	1.25	10	44	
129.00	135.00	6.00		100	749	f	1	<4	55	2	10	1.80	32	20	
135.00	137.00	2.00		100	750	s	<1	10	50	<1	<10	1.05	28	38	
137.00	140.00	3.00			751	s	<1	4	115	14	<10	4.6	16	65	
140.00	143.00	3.00			752	s	<1	12	140	20	<10	8.0	4	55	
143.00	145.00	2.00		100	753	s	<1	36	26	40	<10	22.5	10	42	
145.00	148.00	3.00			754	s	<1	24	65	75	15	16.0	12	42	
148.00	151.00	3.00			755	s	<1	12	20	16	15	19.0	6	30	
151.00	158.00	7.00			756	s	<1	90	55	30	<10	17.5	10	50	
158.00	160.00	2.00			757	s	<1	740	60	6	<10	22.5	6	20	
160.00	162.50	2.50		100	758	s	<1	490	265	4	<10	21.5	<4	22	
162.50	164.60	2.10			759	s	<1	550	240	4	<10	27.5	<4	14	
164.60	165.60	1.00			760	s	<1	430	365	4	<10	18.0	4	26	
165.60	167.80	2.20			761	s	<1	250	285	4	<10	23.0	4	24	
167.80	168.80	1.00			762	s	<1	165	325	10	<10	23.0	6	38	
168.80	171.10	2.30			763	s	<1	530	165	6	<10	20.5	<4	18	
171.10	174.10	3.00			764	s	<1	410	150	4	<10	19.5	4	26	
174.10	176.00	1.90		100	765	s	<1	530	135	4	<10	26.5	8	36	
176.00	177.00	1.00		100	766	s	<1	310	135	4	<10	17.5	6	34	
177.00	178.50	1.50		100	767	s	<1	26	12	2	<10	3.4	<4	25	
178.50	179.50	1.00		100	768	s	<1	24	18	2	<10	10.5	<4	90	
179.50	180.80	1.30		100	769	s	<1	26	25	6	<10	12.0	<4	30	
180.80	183.10	2.30			770	s	<1	65	14	6	<10	12.5	<4	34	
183.10	184.45	1.35			771	s	<1	230	36	36	<10	11.0	22	40	
184.45	184.95	0.50		100	772	s	<1	195	34	115	<10	16.0	48	28	
184.95	187.20	2.25		100	773	s	<1	20	10	24	<10	10.5	10	50	
187.20	188.20	1.00		100	774	s	<1	10	4	8	<10	10.0	6	36	
188.20	188.80	0.60		100	775	s	<1	12	6	6	<10	9.5	<4	38	
188.80	191.00	2.20		100	776	s	<1	10	5	6	<10	10.5	<4	55	
191.00	192.60	1.60		100	777	s	<1	<4	7	6	<10	12.5	<4	95	
192.60	195.20	2.60		100	778	s	<1	6	9	4	<10	23.5	40	60	
195.20	197.00	1.80		100	779	s	<1	<4	22	<1	<10	7.4	10	50	
197.00	199.30	2.30		100	780	s	<1	8	20	<1	<10	6.9	10	75	
199.30	208.00				781	f	<1	<4	14	<1	<10	3.1	12	32	

806152